

United States
Department of
Agriculture
Forest Service



Southeastern Forest
Experiment Station

Research Paper
SE-257

Weight, Volume, and Physical Properties of Major Hardwood Species In the Upland-South

Alexander Clark III
Douglas R. Phillipa
Douglas J. Foderick



November 1986

Southeastern Forest Experiment Station
P. O. Box 2680
Asheville, NC 28802

**Weight, Volume, and Physical Properties
of Major Hardwood Species
in the Upland-South**

Alexander Clark III, Wood Scientist
Southeastern Forest Experiment Station
Athens, Georgia

Douglas R. Phillips, Mensurationist
Southeastern Forest Experiment Station
Clemson, South Carolina

and

Douglas J. Frederick, Professor
School of Forest Resources
North Carolina State University
Raleigh, North Carolina

Procedure	
Field	2
Laboratory	3
Analysis	4
Results	
Physical Properties of Sample Trees	6
Prediction Equations	7
How to Use Prediction Equations	8
Literature Cited	II
Tables (for hardwood species in the Upland-South)	
1. Mean and range of tree age and measurements, by species and tree size class	12
2. Average specific gravity of wood, bark, and wood and bark combined, by tree component and size class	14
3. Average moisture content of wood, bark, and wood and bark combined, by tree component and size class	18
4. Average proportion of wood and bark green weight in bark, by tree component and size class	22
5. Average green weight per cubic foot of wood, bark, and wood and bark combined, by tree component and size class	23
6. Average green weight of wood and bark per cubic foot of wood, by tree component and size class	27
7. Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone, with d.b.h. as the independent variable	28
8. Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone, with d.b.h. as the independent variable	31
9. Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone, with d.b.h. as the independent variable	33
10. Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone, with d.b.h. as the independent variable	34

11.	Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone, with d.b.h. and total height as independent variables	35
12.	Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone, with d.b.h. and total height as independent variables	38
13.	Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone, with d.b.h. and total height as independent variables	40
14.	Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone, with d.b.h. and total height as independent variables	41
15.	Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone, with d.b.h. and height to a 4-inch top as independent variables	42
16.	Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone, with d.b.h. and height to 4-inch top as independent variables	45
17.	Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone, with d.b.h. and height to 4-inch top as independent variables	47
18.	Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone, with d.b.h. and height to 4-inch top as independent variables	48
19.	Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone, with d.b.h. and saw-log merchantable height as independent variables	49
20.	Regression equations for estimating green and dry weight of saw-log merchantable-stem wood and bark combined and wood alone, with d.b.h. and saw-log merchantable height as independent variables	50
21.	Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone, with d.b.h. and saw-log merchantable height as independent variables	51
22.	Regression equations for estimating cubic-foot volume of saw-log merchantable-stem wood and bark combined and wood alone, with d.b.h. and saw-log merchantable height as independent variables	51

23.	Regression coefficients for estimating above-stump stem weight to a specified d.o.b. top diameter as a proportion of total-stem weight	52
24.	Regression coefficients for estimating above-stump stem volume to a specified d. o. b. top diameter as a proportion of total-stem volume	53
25.	Regression coefficients for estimating stem weight to a specified d. o. b. top diameter as a proportion of saw-log stem weight	54
26.	Regression coefficients for estimating stem volume to a specified d. o. b. top diameter as a proportion of saw-log stem volume	55

ABSTRACT

Weight, volume, and physical properties of trees 1 to 20 inches d.b.h. were determined for sweetgum, yellow-poplar, hickory, post oak, scarlet oak, southern red oak, and white oak in Alabama, Mississippi, Arkansas, Kentucky, and Tennessee. Equations for hard hardwoods, soft hardwoods, and individual species are presented for predicting green and dry weight and green volume of the total tree above stump and its components. Input variables are d.b.h. and total height, d.b.h. and height to a 4-inch top, d.b.h. and saw-log merchantable height, or d.b.h. alone. Equations were developed by destructive sampling of 486 trees at 15 locations. Average specific gravity, moisture content, and weight per cubic foot of wood, bark, and wood and bark combined are presented for each species by tree size class and component. Bark percentage is also presented for each species by tree size class and component.

Keywords: Biomass, equations, specific gravity, moisture content, bark percentage, weight per cubic foot.

Hardwood forests of the Upland-South are underutilized. Harvests of wood for energy and fiber products could be increased many fold in these forests, and growth of high-quality sawtimber trees could be improved in the process. Increased utilization of Upland-South hardwoods for low-value fiber and energy products, however, is unlikely in the absence of reliable data on the resource. Until now, however, few data have been available on the weight, volume, and physical properties of total trees and their components for hardwood species of this region.

To meet this need, a nationwide study was initiated by the North Carolina State Hardwood Research Cooperative and the USDA Forest Service with partial funding from the Tennessee Valley Authority's Southeastern Regional Biomass Energy Program, and the Department of Energy. The primary objectives of this study were to determine the amount and distribution of biomass in even-aged fully stocked natural stands and to develop equations for estimating the weight and volume of forest stands, individual trees, and tree components. Secondary objectives were to determine the specific gravity, moisture content, and energy potential of Upland-South hardwoods.

For this study, the South was divided into three geographic regions--the Gulf and Atlantic Coastal Plains, the Piedmont Plateau, and the Upland-South. The data collected in the Gulf and Atlantic Coastal Plains and Piedmont have been reported in earlier publications (Clark and others 1983, 198510, 1986; Frederick and others 1983; Gower and others 1983; Messina and others' 1983, Megalos and others 1986).

This Paper presents tree physical properties and green weight, dry weight, and green cubic-volume prediction equations for total tree and trees components of seven species --sweetgum (Liquidambar styraciflua L.), yellow-poplar (Liriodendron tulipifera L.), hickory species (Carya spp.), post oak (Quercus stellata Wangenh.), scarlet oak (Q. coccinea Muenchh.), southern red oak (Q. falcata Michx.), and white oak (Q. alba L.) sampled in the Upland-South.

Other species were also sampled but not in sufficient number for reliable predicting of their weights and volumes in separate equations. Values for red maple (Acer rubrum L.), silver maple (A. saccharinum L.), blackgum (Nyssa sylvatica var. biflora (Walt.) Sary.), and sycamore (Platanus occidentalis L.) trees are included in the soft-hardwood averages presented. Dogwood (Cornus florida L.), white ash (Fraxinus americana L.), cherrybark oak (Quercus falcata var. pagodifolia Ell.), chestnut oak (Q. prinus L.) and other minor species data are included in the hard-hardwood averages.

Wood and bark specific gravity, moisture content, bark content, and green weight per cubic foot are presented for the total tree and its components by species and tree size classes. Equations are given for estimating the weight and volume of wood, bark, and foliage, wood and bark and wood only in the total tree, total stem, and the saw-log component of the stem. Katio equations are also included for estimating total stem and saw-log stem weight or volume to any specified top diameter outside bark (d.o.b.).

Procedure

Field

Biomass was sampled on 12 1/10-acre circular plots in mixed, even-aged hardwood stands in the Upland-South (fig. 1). Three age classes (20, 40, and 60 years) were sampled on two site types:

Bottom land. Flood plain areas of major drainage systems and adjacent stream margins, predominantly sandy loam to silt loam surface soils.

Upland (slopes and ridges). Land occupying the large upland interstream divides, predominantly clay to sandy clay loam surface soils.




Figure 1.--Locations of plots where trees were sampled on bottom-land sites (B), ridge and upland sites (R), and supplemental (S) locations.

Age and site combinations were replicated twice. Plots for all ages and site types were randomly located within representative fully stocked stands. Tree data collected on all plots were used to develop the species equations and properties data reported here. In addition to samples taken on the fixed-area plots, a stratified random sample of three trees per 2-inch class from 6- to 20-inches in diameter at breast height (d.b.h.) was taken at each of three locations to obtain an even distribution of trees across d.b.h. classes for commercially important species. Figure 1 shows the location of the fixed area and stratified random sample plots.

Weights and volumes of entire trees above stumps and of tree components were collected for trees 1 inch d.b.h. and larger. All trees > 5.0 inches d.b.h. on the 1/10-acre plots were sampled. At the center of each plot, a concentric 1/50-acre subplot was located on which all trees 1.0 to 4.9 inches d.b.h. were sampled.

Means and ranges in age and physical dimensions of measured trees are shown in table 1 for each species and species group sampled. Stump height averaged 0.2 foot for trees 1.0 to 4.9 inches d.b.h., 0.6 foot for trees 5.0 to 10.9 inches d.b.h., and 1.0 foot for trees > 11.0 inches d.b.h. Girard form class of the sawtimber-size trees (> 11.0 inches d.b.h.) ranged from 60 to 85 and averaged 76 for the soft hardwoods; it ranged from 64 to 87 and averaged 76 for the hard hardwoods.

Each tree was felled and measured for d.o.b. at 4-foot intervals up the stem. Total height; height to the saw-log top; height to 9-, 4-, and 2-inch d.o.b. tops, and height to base of full live crown were also recorded. Cross-sectional disks of wood and bark were removed from the stem and branches of sample trees for laboratory determination of specific gravity, moisture content, bark percentage, energy value, and nutrient concentration. In all trees > 5.0 inches d.b.h., except sawtimber-quality trees (trees > 11.0 inches d.b.h. with a minimum of one 16-foot grade 3 log), disks were cut at the butt, at breast height, at quarter-points to the 4-inch d.o.b. top, and at the 2-inch top. In sawtimber trees, disks were removed at the butt, at each saw-log bucking point, and at the stem locations where d.o.b. measured 9, 4, and 2 inches. For trees less than 5.0 inches d.b.h., three disks per stem were taken--at stump height and at 25 and 75 percent of total stem height.

The branches of each tree were cut from the stem and placed in four size categories: extra large (> 4.0 inches d.o.b.), large (2.0 to 3.9 inches d.o.b.), medium (0.6 to 1.9 inches d.o.b.), and small (< 0.5 inches d.o.b.). Three cross-sectional disks were cut from randomly selected branches in each size category for analysis in the laboratory. Sample branches were randomly selected and weighed with and without foliage to estimate foliage weight. A subsample of the foliage was taken to determine foliage moisture content and nutrient content.

The stem of each tree was weighed by components (saw logs, pulpwood, and topwood) and the branches of each tree were weighted by size category.

Laboratory

Specific gravity was computed from green volume and oven-dry weight. Moisture content as a percentage of oven-dry weight was computed on the basis of weight loss after samples were dried to a constant weight at 215 °F. Percentage of bark was determined from disks and based on the green weight of sample disks. Moisture content, specific gravity, and percentages of bark in stem, branches, and total tree were calculated by weighting disk values in proportion to the volume of the component they represented. Weighted values for moisture content were used to convert component green weights to oven-dry weights.

For each species, diameter inside bark (d.i.b.) prediction equations were developed from d.o.b. and d.i.b. stem disk measurements and the d.o.b. and height measurements taken at 4-foot intervals up the stem of each tree. The volume of wood in the stem to the saw-log, 9-inch, 4-inch, 3-inch, and 2-inch tops, and to the tip were calculated using Smalian's formula. Green weight per cubic foot of stem bark and branch wood and bark were calculated from weighted values for specific gravity and moisture content with the equation:

$$\text{Green weight per cubic foot} = [1 + \frac{MC}{100}] \cdot SG \cdot C \quad (1)$$

where: MC = weighted moisture content in percent

SG = weighted specific gravity

C = 62.4 pounds (weight of water per cubic foot)

Cubic-foot volume of stem bark and branch wood and bark were computed by dividing green component weight by its green weight per cubic foot. Cubic-foot volume of stem wood and bark combined was computed by adding the volume of bark to the volume of wood.

Analysis

Regression equations were developed to predict green and dry weight of wood, bark, and foliage and green volume of wood and bark in the total tree above stump, in the stem from butt to tip, and in the saw-log stem. Independent variables were diameter at breast height (D), total height (Th), saw-log merchantable height (Mh), and height to a 4-inch d.o.b. top (H4).

A logarithmic transformation (base 10) was used to obtain relatively homogeneous variance, which is assumed in regression analysis. Two equations were developed for the d.b.h., d.b.h. and total height, and d.b.h. and height to 4-inch top--one for trees < 11.0 inches d.b.h. and one for trees > 11.0 inches d.b.h. The 11 inches was not the statistically optimum point to shift from one equation to the other for all species or tree components, but it was the most desirable from a practical standpoint. Hardwood trees < 11 inches in diameter are classified as sapling or pole timber, and trees > 11 inches are classified as sawtimber. The procedure outlined in Draper and Smith (1981) for fitting two linear equations with a known point of intersection was used to develop the following equations:

$$\log Y_p = a + b \log X + E \quad (2)$$

$$\log Y_s = a + b \log (11^2 H) + c \log (D^2 / 11^2) + E \quad (3)$$

where: Y_p = predicted component weight or volume for trees

< 11.0 inches d.b.h.

Y_s = predicted component weight or volume for trees

> 11.0 inches d.b.h.

X = D^2 , $D^2 Th$, or $D^2 H4$

H = Th or H4

D = d.b.h.

E = experimental error

a, b, c = regression coefficients

The following model was used for developing regression equations based on d.b.h. and saw-log merchantable height:

$$\log Y = a + b \log X_1 + c \log X_2 + E \quad (4)$$

where: Y = predicted component weight or volume

$$X_1 = D^2$$

$$X_2 = Mh$$

E = experimental error

a, b, c = regression coefficients

When logarithmic estimates are converted back to original units, they are biased downward because the antilogarithm of an estimated mean is the geometric rather than the arithmetic mean (Cunia 1964). To adjust for this bias, a correction factor was computed and applied to each model by using Baskerville's (1972) procedure. The final equations, including correction factors, were:

$$Y = 10^{a + b \log(D^2) + c \log(Mh) + (S^2_{y,x} \log_e 10)/2} \quad (5)$$

$$Y_p = 10^{a + b \log(D^2H) + (S^2_{y,x} \log_e 10)/2} \quad (6)$$

$$Y_s = 10^{a + b \log(11^2H) + c \log(D^2/11^2) + (S^2_{y,x} \log_e 10)/2} \quad (7)$$

Equations (5), (6), and (7) can be simplified to:

$$Y = a' (D^2) b (Mh) c \quad (8)$$

$$Y_p = a' (D^2H) b \quad (9)$$

$$Y_s = a'' (D^2) b (H) c \quad (10)$$

where: $a' = 10^a + (S^2_{y,x} \log_e 10)/2$

$$a'' = a' (11^2) b - c$$

$S^2_{y,x}$ = error mean square from regression analysis

Comparison of average deviations (actual minus predicted) by d.b.h. classes and the sums of the squared deviations for the single log-log equation and segmented log-log equation showed that segmented log-log equations (9) and (10) gave the best results for the d.b.h., d.b.h. and total height, and d.b.h. and height to 4-inch top independent variable combinations (Clark and others 1985a). Equations (9) and (10) are more complex than a single equation, but the improved accuracy justified their use.

The exponential ratio equation used to estimate the proportion of predicted total-stem weight or volume in a lesser stem section to a specified top d. o. b. was:

$$Y_R = e^a (d^b D^c) \quad (11)$$

where: Y_R = ratio of stem weight or volume to top d. o. b. to

predicted total stem

d = specified stem top diameter in inches

D = tree diameter at breast height in inches

a, b, c = regression coefficients

e = base of natural log = 2.71828

The exponential ratio model shown below was developed to estimate a ratio for expanding saw-log stem weight or volume to any d. o. b. top above the saw-log top.

$$Y_R = e^a \left[(Mh)^b ((1 - (\frac{d}{.78D})^2)^2)^c \right] \quad (12)$$

where: Y_R = ratio of stem weight or volume to specified top d. o. b. to

estimated saw-log stem weight or volume

Mh = saw-log merchantable height in feet

d = specified top diameter in inches

D = tree diameter at breast height in inches

.78 = constant based on average form class

a, b, c = regression coefficients

e = 2.71828 (base of natural log)

Results

Physical Properties of Sample Trees

The average specific gravity of wood and bark by tree component is shown in table 2 for individual species, soft hardwoods, hard hardwoods, and all trees combined. The average total-tree wood specific gravity of the soft-hardwood species was 0.523 for saplings (1.0 to 4.9 inches d.b.h.), 0.466 for pole timber (5.0 to 10.9 inches d.b.h.), and 0.465 for sawtimber (> 11.0 inches d.b.h.). Averages for hard-hardwood species were 0.612 for saplings, 0.632 for pole timber, and 0.613 for sawtimber. Specific gravity of bark was generally lower than that of wood for both soft-hardwood and hard-hardwood species (table 2).

Average moisture contents of wood and bark by tree component and size class are shown in table 3 for the species and species groups sampled. Total-tree wood moisture content for the soft hardwoods averaged 81 percent for saplings, 90 percent for pole timber, and 87 percent for sawtimber. Values for hard hardwoods averaged 66 percent for saplings, 63 percent for pole timber, and 68 percent for

sdwtimber. Hickory had a lower total-tree wood moisture content than the other hard-hardwood species.

For the soft hardwoods, bark moisture content of total trees averaged 84 percent in saplings, 105 percent in poletimber, and 109 percent in sawtimber. For the hard-hardwood species, averages were 74 percent for saplings, 66 percent for poletimber, and 58 percent for sawtimber (table 3).

Table 4 shows the average proportions of total green weight in bark, by tree component and size class, for the species sampled. The percentage of stem weight in bark decreased as stem d. b. h. increased. For example, the proportion of total-tree green weight in bark averaged 20 percent for saplings, 16 percent for poletimber, and 13 percent for sawtimber in the soft-hardwood group. In the hard-hardwood group, proportions in bark averaged 21 percent for saplings, 18 percent for poletimber, and 17 percent for sawtimber.

The average green weights per cubic foot of wood, bark, and wood and bark combined, by tree component, for saplings, poletimber, and sawtimber are shown in table 5. The average green weight per cubic foot of wood for the soft-hardwood species was 59 pounds for sapling, 55 pounds for poletimber, and 54 pounds for sawtimber. Values for hard hardwoods were 61 pounds for saplings, and 62 pounds for poletimber and sawtimber hard hardwoods.

The average green weight of wood and bark per cubic foot of wood is shown by tree component for saplings, poletimber, and sawtimber-size trees in table 6. The weight of wood and bark per cubic-foot volume of wood is a useful factor for estimating the volume of wood in a tree or its components when weight of wood and bark is known or for estimating green weight of wood and bark when volume of wood is known. The green weight of wood and bark per cubic foot of wood for the total tree averaged 66 pounds for poletimber and 62 pounds for sawtimber in soft hardwoods compared with 76 pounds for poletimber and sawtimber in hard hardwoods.

The average green weight of wood and bark per cubic foot of wood was highest for branches and decreased with increasing stem diameter (table 6).

Prediction Equations

A series of equations was developed to predict total-tree and tree-component weights and volumes for each species, for the soft hardwood and hard hardwood groups, and for all species combined. Equations were developed for predicting the green and dry weight of wood, bark and foliage, wood and bark combined, and wood alone in the above-stump total tree. Stem equations were developed for estimating the green and dry weight of wood and bark combined and wood alone for the total stem. Volume equations were also developed for wood and bark combined and wood alone in the above-stump total tree and total stem.

Since tree height is measured to different top limits by various organizations, equations were developed by using diameter (D) alone and in combination with total height (Th), height to 4-inch top (H4), and merchantable height (Mh) as independent variables. Equation (9) was used to estimate the weight and volume of the total tree and stem for trees 1.0 to 10.9 inches d. b. h., and equation (10) was used for trees > 11.0 inches d. b. h. when D alone, D and Th, or D and H4 were the independent variables.

Equation (8) was used to estimate weight and volume of the total tree and saw-log merchantable stem for trees > 11.0 inches d.b.h. when D and Mh were the independent variables. Equations based on D and Mh were developed only for

species sampled sufficiently in the sawtimber diameter classes. Equations were developed for the soft hardwoods, hard hardwoods, scarlet oak, southern red oak, and all species combined.

Equation (11) was used to estimate the proportion of total weight or volume in the stem to selected d. o. b. tops when stem weight or volume was estimated with D, D and Th, or D and H4 as the independent variables. Equation (12) was used to estimate a ratio for expanding estimated saw-log stem weight or volume to selected d. o. b. tops above the saw-log top when D and M_h were the independent variables.

Equations that use D with Th or D with H4 fit the existing total-tree and total-stem weight and volume data well, based on the criteria of mean square error and absolute deviation of observed from predicted values. Equations that use D and M_h also fit existing saw-log merchantable-stem weight and volume data well. When average tree height and stem taper are similar to those of our sample trees, the equations with D alone will result in good estimates of the tree weight and volume. When average tree heights by d. b. h. class are different from the sample trees, however, the equations that include a height variable should be applied directly or used to develop local weight-volume tables based on D alone.

Regression coefficients for estimating species and species group weight and volume are listed in tables 7 through 22. Each table contains a series of equations for a specific independent variable, tree component and unit of measure (weight or volume). Listed below is a guide to the tables by independent variable, unit of measure, tree component, and table number.

Independent variable	Weight			Volume		
	Total tree	Total stem	Saw-log stem	Total tree	Total stem	Saw-log stem
D alone	7	8		9	10	
D and Th	11	12		13	14	
D and H4	15	16		17	18	
D and M _h	19		20	21		22

In addition to the regression coefficients, tables 7 through 22 contain the coefficients of determination (R^2) and standard error ($S_{y,x}$, log.) for each equation.

Regression coefficients for estimating the proportion of the total-stem weight and volume in the stem to a specified d. o. b. top are given in tables 23 and 24. Table 23 contains coefficients for estimating ratios for stem green and dry weight of wood and bark combined and wood only, and table 24 contains the coefficients for stem volume of wood and bark combined and wood alone. Equation coefficients for expanding estimated weights and volumes of saw-log merchantable stems are shown in tables 25 and 26.

How to Use Prediction Equations

Use of the coefficients in tables 7 through 26 to estimate the weight and volume is best illustrated through examples.

Assume that we have two soft hardwood trees and we want to estimate the green weight of their stems with bark to a 4-inch d.o.b. top. The first tree has a d.b.h. of 10.0 inches and a total height of 70 feet and the second tree measures 14.0 inches d.b.h. and 90 feet in total height. To estimate stem weight to a 4-inch top, we must first estimate total stem weight and then estimate the proportion of total stem weight in the stem to a 4-inch d.o.b. top.

Since our independent variables are d.b.h. and total height and we want to estimate the weight of the total stem, we would select our regression coefficients from table 12 as shown by the above guide. Since our 10.0-inch d.b.h. tree is less than 11.0 inches d.b.h., we would use the a' and b coefficients listed for soft hardwoods under trees < 11.0 inches d.b.h. and the equation for trees < 11.0 inches d.b.h. at the bottom of table 12. To estimate total stemwood and bark green weight (Y_{STEMWB}), we would substitute our trees' d.b.h., total height, and the regression coefficients into the equation for trees < 11.0 inches d.b.h. and solve as follows:

$$\begin{aligned} Y_{STEMWB} &= a' (D^2 Th)^b \\ &= 0.25113 ((102) (70))^{0.91865} \\ &= 0.25113 (7000)^{0.91865} \\ &= 0.25113 (3,406.43) \end{aligned}$$

$$Y_{STEMWB} = 855 \text{ pounds}$$

To estimate the total stem weight of our 14-inch tree, we would use the soft hardwood coefficients listed for trees \geq 11.0 inches d.b.h. and the equation for trees \geq 11.0 inches d.b.h. at the bottom of table 12 and solve as follows:

$$\begin{aligned} Y_{STEMWB} &= a'' (D^2)^b (Th)^c \\ &= 0.22629 (142)^{0.94037} (90)^{0.91865} \\ &= 0.22629 (196)^{0.94037} (90)^{0.91865} \\ &= 0.22629 (143.08) (62.41) \end{aligned}$$

$$Y_{STEMWB} = 2,021 \text{ pounds}$$

The same mathematical procedure shown above would be used to solve any of the tree component equations in tables 7 through 18.

To estimate the proportion of total-stem wood and bark green weight of our 10-inch tree in the stem to a 4-inch top, we would use the ratio equation shown in table 23 and the green-weight coefficients for soft hardwoods. We would solve the equation as follows:

$$\begin{aligned} Y_R &= e^a (d)^b (D)^c \\ &= 2.71828 - 1.66655 (4)^{4.50927} (10) - 4.50649 \\ &= 2.71828 - 1.66655 (518.62) (0.0000312) \\ &= 2.71828 - 0.02693 \end{aligned}$$

$$Y_R = 0.973$$

$$\begin{aligned} \text{Stem weight to 4-inch top} &= (Y_{\text{STEMWB}}) (Y_r) \\ &= 855 (0.973) \end{aligned}$$

$$\text{Stem weight to 4-inch top} = 832 \text{ pounds}$$

The procedure shown above can be used to estimate the proportion of total stem in the stem to any d.o.b. top by substituting for d in the above equation.

In a second example, assume we have a 14.0-inch 2-log soft hardwood tree and we want to estimate the green weight of wood and bark in the saw-log merchantable stem (Y_{SAWWB}). Since our independent variables are D and Mh and we want to estimate the weight of the saw-log merchantable stem, we would use the soft-hardwood coefficients and equation listed in table 20. To use the D and Mh equation, Mh must be in feet. Thus:

$$Mh = 33.1 \text{ feet} = (2.0 \text{ logs}) (16.3 \text{ ft/log}) + (0.5 \text{ ft for stump})$$

We would then solve the D and Mh equation as follows:

$$\begin{aligned} Y_{\text{SAWWB}} &= a^b (D^2)^c (Mh)^d \\ &= 0.67303 (14)^{0.84073} (33.1)^{0.90211} \\ &= 0.67303 (84.56) (23.50) \end{aligned}$$

$$Y_{\text{SAWWB}} = 1,337 \text{ pounds}$$

The same mathematical procedure shown above would be used to solve any of the D and Mh equations in tables 19 through 22.

To estimate a ratio (Y_R) for expanding estimated saw-log merchantable-stem green weight of wood and bark of the previous example tree to weight to a 4-inch d.o.b. top, the following soft-hardwood ratio equation would be selected from table 25 and solved as shown below:

$$\begin{aligned} Y_R &= e^a \left[(Mh)^b ((1 - (\frac{d}{78D})^2)^2)^c \right]^{0.38432} \\ &= 2.718288 \cdot 47209 \left[(33.1)^{-0.87551} ((1 - (\frac{4}{78(14)})^2)^2)^{0.38432} \right] \\ &= 2.718288 \cdot 47209 (0.04671) (0.89517) \\ &= 2.718280 \cdot 35425 \end{aligned}$$

$$Y_R = 1.425$$

$$\begin{aligned} \text{Stem weight to 4-inch top} &= (Y_{\text{SAWWB}}) (Y_r) \\ &= 1,337 (1.425) \end{aligned}$$

$$\text{Stem weight to 4-inch top} = 1,905 \text{ pounds}$$

The tree components predicted by using the equations provided can be used to calculate additional tree components. For example, to estimate the weight or volume of the crown (branches and topwood), subtract estimated weight of the stem to a specified d.o.b. top from total-tree weight of wood and bark. The weight or volume of bark alone can also be estimated by subtracting component weight or volume of wood from wood and bark.

Similar-size trees may vary in weight and volume because of differences in crown size, stem taper, and weight per cubic foot. Therefore, these equations should be applied only to trees growing in natural, fully stocked stands with tree dimensions and weight per cubic foot similar to the tree sampled.

Literature Cited

- Baskerville, G. L. Use of logarithmic regression in the estimation of plant biomass. Canadian Journal of Forest Research 2:49-53; 1972.
- Clark, Alexander, III; Muse, H. David; Phillips, Douglas R.; Frederick, Douglas J. Use of segmented log-log equations to estimate tree biomass. In: Saucier, Joseph R., ed. Proceedings of the 1984 southern forest biomass workshop. Sixth annual meeting of the Southern Forest Biomass Working Group; 1984 June 5-7; Athens, GA. Asheville, NC: U.S. Department of Agriculture, Forest Service, Southeastern Forest Experiment Station; 1985a: 51-57.
- Clark, Alexander, III; Phillips, Douglas R.; Frederick, Douglas J. Biomass distribution and production of Coastal Plain hardwood stands. In: Energy from biomass and wastes 7: proceedings of Institute of Gas Technology symposium; 1983 January 24-28; Lake Buena Vista, FL; 1983: 101-115. [Available from Institute of Gas Technology, Chicago, IL]
- Clark, Alexander, III; Phillips, Douglas R.; Frederick, Douglas J. Weight, volume, and physical properties of major hardwood species in the Gulf and Atlantic Coastal Plains. Res. Pap. SE-250. Asheville, NC: U.S. Department of Agriculture, Forest Service, Southeastern Forest Experiment Station; 1985b. 66 pp.
- Clark, Alexander, III; Phillips, Douglas R.; Frederick, Douglas J. Weight, volume, and physical properties of major hardwood species in the Piedmont. Res. Pap. SE-255. Asheville, NC: U.S. Department of Agriculture, Forest Service, Southeastern Forest Experiment Station; 1986. 78 pp.
- Cunia, T. Weighted least squares method and construction of volume tables. Forest Science 10:180-191; 1964.
- Draper, N.R.; Smith, H. Applied regression analyses. 2d ed. New York: John Wiley & Sons, Inc.; 1981. 709 pp.
- Frederick, Douglas J.; Clark, Alexander, III; Phillips, Douglas R. Biomass, nutrient and energy relationships of Coastal Plain hardwoods. In: The hardwood resource and its utilization: where are we going?: 11th annual hardwood symposium of the Hardwood Research Council; 1983 May 10-13; High Hampton, NC; 1983:139-147. [Available from U.S. Department of Agriculture, Forest Service, Southern Forest Experiment Station, New Orleans, LA]
- Gower, S. T.; Frederick, D.J.; Clark, A., III. Caloric content estimation and distribution in seven bottomland hardwood tree species growing in natural stands in the South. In: Proceedings: fourth central hardwood forest conference; 1982 November 8-10; Lexington, KY: University of Kentucky; 1983: 384-390.
- Megalos, M.A.; Frederick, D.J.; Clark, A.; Phillips, D.R. Biomass, nutrient, and energy content of southern Piedmont hardwood forests. Hardwood Research Cooperative Series No. 5. Raleigh, NC: North Carolina State University; 1986. 34 pp.
- Messina, M.G.; Gower, S.T.; Frederick, D.J.; Clark, A., III; Phillips, D.R. Biomass, nutrient, and energy content of southeastern wetland hardwood forests. Hardwood Research Cooperative Series No. 2. Raleigh, NC: North Carolina State University; 1983. 28 pp.

Table 1. -- Mean and range of tree age and measurements, by species and tree size class

Tree size class (inches)	Sample trees	Age		D.b.h.		Total height	Height to 4- inch d. o. b. top			Height to saw- log merchantable top			D. o. b. at saw- log merchantable top			
		Average	Range	Average	Range		Average	Range	Average	Average	Range	Average	Average	Range		
<u>Number</u>												<u>Inches</u>				
SOFT HARDWOODS												<u>Feet</u>				
1.0- 4.9	40	21	a-55	6.7	1.3- 4.9	31	15- 52	--	--	--	--	--	--	--	--	
5.0-10.9	54	31	13-64	14.6	11.0-19.3 5.0-10.4	59	35-104	32	8-80	--	--	--	--	--	--	
>11.0	28	45	36-65			96	78-112	75	49-87	41	21-68					
All trees	122	32	8-65	7.2	1.3-19.3	59	15-112	44	1-87	41	21-68	10.0	9.0-14.0	10.0	9.0-14.0	
SWEETGUM												<u>Inches</u>				
1.0- 4.9	10	20	9-55	3.4	1.9- 4.9	39	25- 52	--	--	--	--	--	--	--	--	
5.0-10.9	20	28	15-57	6.6	5.2- 8.5	61	44- 89	32	12-63	--	--	--	--	--	--	
>11.0	9	51	40-65	14.5	11.0-17.2	93	78-108	73	49-87	38	21-50	10.6	9.0-13.1	10.6	9.0-13.1	
All trees	39	32	9-65	7.6	1.9-17.2	63	25-108	41	4-87	38	21-50	10.6	9.0-13.1	10.6	9.0-13.1	
YELLOW-POPLAR												<u>Feet</u>				
5.0-10.9	10	30	19-38	7.7	5.3-10.2	69	48-104	46	20-80	--	--	--	--	--	--	
>11.0	9	39	37-41	15.0	12.0-18.7	105	48-112	82	75-87	52	37-68	9.8	9.0-12.4	9.8	9.0-12.4	
All trees	19	34	19-41	11.1	5.3-18.7	86	48-103	63	20-87	52	37-68	9.8	9.0-12.4	9.8	9.0-12.4	
HARD HARDWOODS												<u>Inches</u>				
1.0- 4.9	102	21	9- 53	2.3	1.0- 4.9	28	10- 50	--	--	--	--	--	--	--	--	
5.0-10.9	191	46	15-100	7.4	5.0-10.9	54	31- 88	30	7-68	--	--	--	--	--	--	
>11.0	71	77	22-130	14.9	11.0-22.0	71	50-103	52	34-86	27	12-45	11.5	8.6-16.9	11.5	8.6-16.9	
All trees	364	48	9-130	7.4	1.0-22.0	50	10-103	35	2-86	27	12-45	11.5	8.6-16.9	11.5	8.6-16.9	
HICKORY												<u>Feet</u>				
1.0- 4.9	15	24	14- 40	6.9	1.0- 4.7	25	10- 42	--	--	--	--	--	--	--	--	
5.0-10.9	20	55	19- 93	16.1	15.0-10.8	50	32- 88	24	7-64	--	--	--	--	--	--	
>11.0	83	83	66-100			88	72-103	71	55-86	31	27-34	13.5	12.0-14.9	13.5	12.0-14.9	
All trees	3:	47	14-100	5.4	1.0-18.1	42	10-103	27	7-86	31	27-34	13.5	12.0-14.9	13.5	12.0-14.9	

Continued

Table 1.--Mean and range of tree age and measurements, by species and tree size class--Continued

Tree size class (inches)	Sample trees	Age		D.b.h.		Total height	Height to 4- inch d. o. b. top		Height to saw- log merchantable top		D. o. b. at saw- log merchantable top	
		Average	Range	Average	Range		Average	Range	Average	Range	Average	Range
		<u>Number</u>		<u>Inches</u>		<u>Feet</u>						<u>Inches</u>
						POST OAK						
5.0-10.9	14	54	41-100	6.7	5.1-10.2	57	33-66	23	10-49	--	--	--
> 11.0	12	110	88-130	14.4	11.2-20.9	51	33-50-66	43	36-54	24	12-35	10.2
All trees	26	80	41-130	10.3	5.1-20.9			32	10-54	24	12-35	10.2
		SCARLET OAK										
5.0-10.9	24	44	36-65	8.1	5.1-10.9	60	45-73	35	17-51	--	--	--
> 11.0	17	63	39-98	15.0	11.5-20.0	79	58-94	57	42-69	30	13-45	11.7
All trees	42	52	36-98	10.8	4.8-20.0	68	45-94	44	16-69	30	13-45	11.7
		SOUTHERN RED OAK										
5.0-10.9	17	51	37-74	8.2	5.4-10.2			36	13-54	--	--	--
> 11.0	17	69	44-100	15.6	11.3-22.0	7:	68-53-84	54	45-65	24	18-35	12.5
All trees	34	60	37-100	11.9	5.4-22.0	69	53-84	45	13-65	24	18-35	12.5
		WHITE OAK										
1.0- 4.9	12	27	14- 53	3.2	1.3- 4.7	34	16- 47	--	--	--	--	--
5.0-10.9	65	48	27- 76	7.0	5.0-10.6	64	31- 69	26	7-52	--	--	--
> 11.0	10	98	53-112	17.1	13.3-20.5	49	53-16-74	48	37-57	29	21-38	12.4
All trees	87	51	14-112	7.7	1.3-20.5			28	5-57	29	21-38	11.8
		ALL SPECIES										
1.0- 4.9	142	21	8- 55	2.4	1.0- 4.9	29	10- 52	--	--	--	--	--
5.0-10.9	245	43	13-100	7.2	5.0-10.9	55	31-104	30	7-80	--	--	--
> 11.0	99	68	22-130	14.9	11.0-22.0	78	50-112	59	34-87	31	12-68	11.1
All trees	486	43	8-130	7.4	1.0-22.0	52	10-112	37	1-87	30	12-68	10.9

Table 2.--Average specific gravity of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to Y-inch top	Y-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches			
SOFT HARDWOODS										
Wood										
1.0- 4.9	0.523 \pm 0.042	--	--	--	--	0.529 \pm 0.047	0.489 \pm 0.038			
5.0-10.9	0.466 \pm 0.054	0.455 \pm 0.029	0.471 \pm 0.057	0.471 \pm 0.057	0.461 \pm 0.054	0.468 \pm 0.058	0.464 \pm 0.051			
\geq 11.0	0.465 \pm 0.041	0.464 \pm 0.044	0.464 \pm 0.040	0.464 \pm 0.042	0.477 \pm 0.034	0.464 \pm 0.042	0.473 \pm 0.040			
Bark										
1.0- 4.9	0.445 \pm 0.065	--	--	--	--	0.456 \pm 0.082	0.423 \pm 0.046			
5.0-10.9	0.407 \pm 0.072	0.419 \pm 0.090	0.405 i-0.095	0.405 \pm 0.095	0.418 \pm 0.078	0.406 \pm 0.088	0.421 \pm 0.053			
\geq 11.0	0.422 \pm 0.068	0.418 \pm 0.079	0.430 \pm 0.078	0.423 \pm 0.077	0.429 \pm 0.062	0.424 \pm 0.076	0.419 \pm 0.055			
Wood and Bark										
1.0- 4.9	0.507 \pm 0.039	--	--	--	--	0.514 \pm 0.046	0.468 \pm 0.031			
5.0-10.9	0.457 \pm 0.051	0.442 i-0.032	0.459 \pm 0.054	0.459 \pm 0.054	0.451 \pm 0.050	0.459 \pm 0.055	0.450 \pm 0.046			
\geq 11.0	0.459 \pm 0.042	0.458 \pm 0.044	0.458 \pm 0.043	0.458 \pm 0.043	0.467 \pm 0.035	0.459 \pm 0.044	0.459 \pm 0.038			
SWEETGUM										
Wood										
1.0- 4.9	0.485 \pm 0.022	--	--	--	--	0.485 \pm 0.022	0.488 \pm 0.058			
5.0-10.9	0.481 \pm 0.027	0.484 \pm 0.000	0.486 \pm 0.028	0.486 \pm 0.028	0.472 \pm 0.032	0.480 \pm 0.028	0.476 \pm 0.028			
\geq 11.0	0.498 \pm 0.015	0.497 \pm 0.016	0.493 \pm 0.019	0.496 \pm 0.017	0.500 \pm 0.026	0.496 \pm 0.017	0.510 \pm 0.018			
Bark										
1.0- 4.9	0.370 \pm 0.031	--	--	--	--	0.369 \pm 0.030	0.376 \pm 0.047			
5.0-10.9	0.388 \pm 0.040	0.419 \pm 0.000	0.370 \pm 0.047	0.370 \pm 0.047	0.421 \pm 0.040	0.384 \pm 0.045	0.421 \pm 0.036			
\geq 11.0	0.418 \pm 0.027	0.406 \pm 0.035	0.428 \pm 0.045	0.417 \pm 0.032	0.446 \pm 0.026	0.418 \pm 0.030	0.419 \pm 0.021			
Wood and Bark										
1.0- 4.9	0.465 \pm 0.021	--	--	--	--	0.465 \pm 0.022	0.449 \pm 0.044			
5.0-10.9	0.467 \pm 0.024	--	0.467 \pm 0.023	0.467 \pm 0.023	0.462 i-0.030	0.468 \pm 0.025	0.458 \pm 0.021			
\geq 11.0	0.488 \pm 0.015	0.485 \pm 0.015	0.482 \pm 0.019	0.484 \pm 0.017	0.489 \pm 0.020	0.487 \pm 0.017	0.487 \pm 0.013			
YELLOW-POPLAR										
Wood										
5.0-10.9	0.389 \pm 0.052	0.441 \pm 0.031	0.389 \pm 0.053	0.390 \pm 0.053	0.392 \pm 0.053	0.388 \pm 0.050	0.402 \pm 0.071			
\geq 11.0	0.412 \pm 0.020	0.409 \pm 0.027	0.414 \pm 0.023	0.410 \pm 0.020	0.445 \pm 0.023	0.410 \pm 0.020	0.428 \pm 0.1120			
Bark										
5.0-10.9	0.350 \pm 0.018	0.346 \pm 0.016	0.345 \pm 0.019	0.345 \pm 0.019	0.350 \pm 0.023	0.345 \pm 0.019	0.365 \pm 0.053			
\geq 11.0	0.344 \pm 0.017	0.330 \pm 0.017	0.342 \pm 0.019	0.336 \pm 0.018	0.352 \pm 0.018	0.337 \pm 0.018	0.356 \pm 0.026			

Continued

Table 2 .-- Average specific gravity of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						
		Stem						
		autt to Y-inch top	Y-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches	
Wood and Bark								
5.0-10.9	0.383 \pm 0.045	0.425 \pm 0.023	0.345 \pm 0.019	0.345 \pm 0.019	0.350 \pm 0.023	0.345 \pm 0.019	0.365 \pm 0.053	
\geq 11.0	0.404 \pm 0.018	0.400 \pm 0.024	0.402 \pm 0.018	0.400 \pm 0.018	0.427 \pm 0.019	0.401 \pm 0.018	0.410 \pm 0.015	
HARD HARDWOODS								
Wood								
1.0- 4.9	0.612 \pm 0.040							
5.0-10.9	0.632 \pm 0.049	0.613 I- 0.062	0.631 \pm 0.051	0.631 i- 0.051	0.634 i- 0.048	0.617 \pm 0.041	0.578 \pm 0.045	
\geq 11.0	0.613 \pm 0.031	0.596 \pm 0.040	0.622 \pm 0.031	0.600 \pm 0.034,	0.649 \pm 0.027	0.631 \pm 0.049	0.639 \pm 0.055	
Bark								
1.0- 4.9	0.483 \pm 0.083	--	--					
5.0-10.9	0.541 \pm 0.061	0.552 \pm 0.067	0.561 \pm 0.075	0.559 i- 0.072	0.548 \pm 0.067	0.498 \pm 0.094	0.443 \pm 0.063	
\geq 11.0	0.582 \pm 0.077.	0.596 \pm 0.087	0.599 \pm 0.098	0.596 \pm 0.088	0.582 \pm 0.080	0.558 \pm 0.071	0.511 \pm 0.078	
Wood and Bark								
1.0- 4.9	0.587 \pm 0.035	--	--					
5.0-10.9	0.616 \pm 0.042	0.597 \pm 0.058	0.619 \pm 0.044	0.619 \pm 0.044	0.616 \pm 0.042	0.594 \pm 0.036	0.533 \pm 0.039	
\geq 11.0	0.609 \pm 0.027	0.596 \pm 0.036	0.619 \pm 0.031	0.600 \pm 0.030	0.633 \pm 0.030	0.620 \pm 0.043	0.596 \pm 0.048	
HICKORY								
Wood								
1.0- 4.9	0.642 \pm 0.050	--	--					
5.0-10.9	0.651 \pm 0.043	0.622 \pm 0.029	0.663 \pm 0.043	0.662 \pm 0.044	0.656 \pm 0.050	0.655 \pm 0.055	0.557 \pm 0.038	
\geq 11.0	0.624 \pm 0.056	0.627 \pm 0.061	0.649 \pm 0.017	0.632 \pm 0.053	0.628 \pm 0.077	0.659 \pm 0.044	0.611 \pm 0.058	
Bark								
1.0- 4.9	0.526 \pm 0.035	--	--					
5.0-10.9	0.528 \pm 0.044	0.529 \pm 0.045	0.554 \pm 0.050	0.554 Fo. 049	0.524 \pm 0.058	0.536 \pm 0.036	0.465 \pm 0.031	
\geq 11.0	0.511 \pm 0.048	0.528 \pm 0.054	0.542 \pm 0.040	0.530 \pm 0.050	0.498 \pm 0.071	0.548 \pm 0.053	0.479 \pm 0.030	
Wood and Bark								
1.0- 4.9	0.607 \pm 0.038	--	--					
5.0-10.9	0.625 \pm 0.039	0.617 \pm 0.019	0.640 \pm 0.040	0.640 \pm 0.040	0.625 \pm 0.045	0.615 \pm 0.041	0.521 \pm 0.028	
\geq 11.0	0.605 \pm 0.052	0.613 \pm 0.057	0.631 \pm 0.021	0.617 \pm 0.050	0.593 \pm 0.086	0.637 \pm 0.042	0.563 \pm 0.044	
POST OAK								
Wood								
5.0-10.9	0.678 \pm 0.028	0.650 \pm 0.047	0.672 \pm 0.039	0.673 \pm 0.036	0.664 \pm 0.1142	0.671 \pm 0.035	0.703 \pm 0.025	
\geq 11.0	0.646 \pm 0.020	0.634 \pm 0.028	0.645 \pm 0.029	0.635 \pm 0.027	0.668 \pm 0.027	0.635 \pm 0.027	0.679 \pm 0.023	

Table 2.--Average specific gravity of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						
		Stem						
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip		Branches
Bark								
5.0-10.9	0.492 \pm 0.063	0.556 \pm 0.119	0.504 \pm 0.073	0.501 \pm 0.064	0.483 \pm 0.077	0.497 \pm 0.066	0.484 \pm 0.065	
> 11.0	0.520 \pm 0.052	0.544 \pm 0.049	0.504 \pm 0.057	0.536 \pm 0.052	0.485 \pm 0.054	0.534 \pm 0.052	0.497 \pm 0.052	
Wood and Bark								
5.0-10.9	0.644 \pm 0.021	0.633 \pm 0.038	0.640 \pm 0.027	0.641 \pm 0.026	0.622 \pm 0.025	0.645 \pm 0.026	0.621 \pm 0.039	
> 11.0	0.626 \pm 0.016	0.621 \pm 0.018	0.622 \pm 0.024	0.620 \pm 0.018	0.622 \pm 0.024	0.623 \pm 0.019	0.620 \pm 0.028	
SCARLET OAK								
Wood								
1.0- 4.9	0.634 \pm 0.000	--	--	--	--	0.639 \pm 0.000	0.556 \pm 0.000	
5.0-10.9	0.622 \pm 0.032	0.609 \pm 0.024	0.613 \pm 0.029	0.612 \pm 0.029	0.630 \pm 0.036	0.614 \pm 0.029	0.652 \pm 0.048	
> 11.0	0.606 \pm 0.022	0.584 \pm 0.025	0.626 \pm 0.027	0.588 \pm 0.025	0.648 \pm 0.022	0.588 \pm 0.025	0.653 \pm 0.026	
Bark								
1.0- 4.9	0.621 \pm 0.000	--	--	--	--	0.636 \pm 0.000	0.477 \pm 0.000	
5.0-10.9	0.606 \pm 0.022	0.607 \pm 0.038	0.643 \pm 0.036	0.635 \pm 0.035	0.608 \pm 0.030	0.631 \pm 0.035	0.548 \pm 0.028	
> 11.0	0.623 \pm 0.028	0.640 \pm 0.032	0.654 \pm 0.030	0.641 \pm 0.031	0.625 \pm 0.035	0.640 \pm 0.031	0.593 \pm 0.038	
Wood and Bark								
1.0- 4.9	0.630 \pm 0.000	--	--	--	--	0.638 \pm 0.000	0.522 \pm 0.000	
5.0-10.9	0.620 \pm 0.028	0.608 \pm 0.017	0.617 \pm 0.025	0.616 \pm 0.026	0.626 \pm 0.031	0.617 \pm 0.026	0.622 \pm 0.037	
> 11.0	0.609 \pm 0.018	0.592 \pm 0.022	0.632 \pm 0.021	0.595 \pm 0.022	0.644 \pm 0.019	0.596 \pm 0.022	0.638 \pm 0.023	
SOUTHERN RED OAK								
Wood								
5.0-10.9	0.605 \pm 0.019	0.607 \pm 0.023	0.593 \pm 0.018	0.596 \pm 0.018	0.618 \pm 0.023	0.597 \pm 0.018	0.653 \pm 0.036	
> 11.0	0.601 \pm 0.020	0.579 \pm 0.022	0.609 \pm 0.022	0.581 \pm 0.021	0.652 \pm 0.028	0.582 \pm 0.021	0.652 \pm 0.021	
Bark								
5.0-10.9	0.602 \pm 0.030	0.592 \pm 0.034	0.623 \pm 0.031	0.613 \pm 0.029	0.623 \pm 0.024	0.616 \pm 0.027	0.556 \pm 0.035	
> 11.0	0.662 \pm 0.026	0.675 \pm 0.026	0.695 \pm 0.024	0.678 \pm 0.025	0.663 \pm 0.035	0.677 \pm 0.025	0.630 \pm 0.042	
Wood and Bark								
5.0-10.9	0.605 \pm 0.015	0.605 \pm 0.015	0.600 \pm 0.014	0.600 \pm 0.013	0.619 \pm 0.020	0.601 \pm 0.014	0.623 \pm 0.036	
> 11.0	0.615 \pm 0.014	0.596 \pm 0.017	0.628 \pm 0.018	0.598 \pm 0.016	0.656 \pm 0.022	0.598 \pm 0.016	0.645 \pm 0.017	

Continued

Table 2--Average specific gravity of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Up and South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip				
WHITE OAK										
Wood										
1.0- 4.9	0.641 \pm 0.022	--	--	--	--	0.646 \pm 0.023	0.594 \pm 0.031			
5.0-10.9	0.654 \pm 0.039	0.659 \pm 0.053	0.654 \pm 0.041	0.654 \pm 0.041	0.650 \pm 0.046	0.652 \pm 0.041	0.656 \pm 0.044			
> 11.0	0.635 \pm 0.007	0.626 \pm 0.011	0.639 \pm 0.012	0.627 \pm 0.011	0.654 \pm 0.013	0.628 \pm 0.011	0.657 \pm 0.021			
Bark										
1.0- 4.9	0.483 \pm 0.048	--	--	--	--	0.484 \pm 0.054	0.473 \pm 0.026			
5.0-10.9	0.518 \pm 0.050	0.530 i-0.047	0.530 \pm 0.052	0.530 \pm 0.054	0.521 \pm 0.056	0.528 \pm 0.053	0.508 \pm 0.113			
> 11.0	0.573 \pm 0.036	0.604 \pm 0.041	0.608 \pm 0.039	0.605 \pm 0.040	0.575 \pm 0.033	0.604 \pm 0.040	0.533 \pm 0.035			
Wood and Bark										
1.0- 4.9	0.607 \pm 0.026	--	--	--	--	0.614 \pm 0.026	0.544 \pm 0.031			
5.0-10.9	0.632 \pm 0.036	0.633 \pm 0.060	0.636 \pm 0.039	0.635 \pm 0.039	0.622 \pm 0.045	0.636 \pm 0.039	0.605 \pm 0.048			
> 11.0	0.626 \pm 0.005	0.624 \pm 0.010	0.633 \pm 0.010	0.625 \pm 0.009	0.635 \pm 0.014	0.625 \pm 0.009	0.622 \pm 0.022			
ALL SPECIES										
Wood										
1.0- 4.9	0.582 \pm 0.058	--	--	--	--	0.588 \pm 0.060	0.549 \pm 0.060			
5.0-10.9	0.595 \pm 0.085	0.601 \pm 0.074	0.595 \pm 0.085	0.595 \pm 0.085	0.598 \pm 0.086	0.597 \pm 0.084	0.601 \pm 0.091			
> 11.0	0.571 \pm 0.075	0.558 \pm 0.072	0.577 \pm 0.079	0.561 \pm 0.072	0.600 \pm 0.083	0.562 \pm 0.072	0.597 \pm 0.087			
Bark										
1.0- 4.9	0.471 \pm 0.079	--	--	--	--	0.484 \pm 0.092	0.436 \pm 0.058			
5.0-10.9	0.511 \pm 0.085	0.541 \pm 0.077	0.526 \pm 0.103	0.525 \pm 0.101	0.521 \pm 0.087	0.526 \pm 0.097	0.491 \pm 0.082			
> 11.0	0.537 \pm 0.104	0.546 \pm 0.117	0.551 \pm 0.120	0.547 \pm 0.115	0.538 \pm 0.102	0.547 \pm 0.114	0.521 \pm 0.090			
Wood and Bark										
1.0- 4.9	0.561 \pm 0.052	--	--	--	--	0.568 \pm 0.054	0.511 \pm 0.048			
5.0-10.9	0.581 \pm 0.079	0.583 i-0.072	0.584 \pm 0.081	0.583 \pm 0.081	0.582 \pm 0.080	0.587 \pm 0.080	0.564 \pm 0.077			
> 11.0	0.567 \pm 0.075	0.557 \pm 0.074	0.574 \pm 0.081	0.560 \pm 0.073	0.586 \pm 0.081	0.561 \pm 0.073	0.575 \pm 0.082			

Table 3.--Average moisture content of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip				
<u>Percent</u>										
SOFT HARDWOODS										
Wood										
1.0- 4.9	81 ± 17.8	--	--	--	--	82 ± 18.3	77 ± 20.1			
5.0-10.9	90 ± 20.2	89 ± 17.6	90 ± 20.4	90 ± 20.4	95 i-22.2	92 ± 20.6	89 ± 21.1			
> 11.0	87 ± 15.2	88 ± 16.6	86 ± 15.4	88 ± 15.9	86 ± 17.1	87 ± 15.8	88 ± 14.2			
Bark										
1.0- 4.9	84 ± 24.7	--	--	--	--	80 ± 27.4	101 ± 30.3			
5.0-10.9	105 ± 28.8	102 ± 29.4	100 ± 31.0	100 ± 30.9	116 ± 35.7	105 ± 30.8	117 ± 30.2			
≥ 11.0	109 ± 26.9	100 ± 27.9	103 ± 32.0	101 ± 29.4	128 ± 28.1	102 ± 2Y.4	128 ± 26.3			
Wood and Bark										
1.0- 4.9	81 ± 18.1	--	--	--	--	81 ± 18.9	84 ± 22.5			
5.0-10.9	92 ± 19.3	89 ± 16.0	92 ± 19.5	92 ± 19.5	98 ± 21.3	94 ± 19.5	97 ± 20.1			
≥ 11.0	90 ± 13.9	90 ± 15.5	89 ± 14.8	89 ± 14.7	94 ± 15.9	90 ± 14.7	97 ± 13.9			
SWEETGUM										
Wood										
1.0- 4.9	104 ± 11.1	--	--	--	--	104 ± 11.4	102 ± 23.2,			
5.0-10.9	103 ± 10.3	107 ± 0.0	103 ± 10.3	103 ± 10.3	106 ± 13.9	104 ± 11.2	101 ± 9.2			
≥ 11.0	99 ± 5.1	102 ± 7.6	98 ± 5.5	100 ± 5.2	92 ± 7.8	100 ± 5.2	94 ± 6.0			
Bark										
1.0- 4.9	120 ± 16.8	--	--	--	--	118 ± 22.6	130 ± 37.2			
5.0-10.9	103 ± 20.3	82 ± 0.0	97 ± 19.9	97 ± 19.9	113 i-28.3	101 ± 21.4	118 ± 23.4			
≥ 11.0	90 ± 7.2	80 ± 11.5	78 ± 7.4	78 ± 7.8	113 ± 19.5	78 ± 7.8	121 ± 16.8			
Wood and Bark										
1.0- 4.9	106 ± 10.7	--	--	--	--	106 ± 11.3	112 ± 26.7			
5.0-10.9	103 ± 10.1	--	102 ± 10.1	102 ± 10.1	107 ± 13.5	103 ± 11.0	106 ± 10.6			
≥ 11.0	98 ± 4.5	99 ± 7.9	94 ± 5.2	97 ± 5.0	97 ± 9.7	98 ± 4.9	101 ± 7.4			
YELLOW-POPLAR										
Wood										
5.0-10.9	100 ± 19.7	85 ± 5.9	100 ± 20.0	100 ± 20.0	106 ± 22.7	100 ± 20.0	100 ± 24.5			
≥ 11.0	89 ± 6.6	91 ± 6.9	88 ± 6.7	90 ± 6.9	Y0 ± 16.9	89 ± 7.0	89 ± 12.1			
Bark										
5.0-10.9	142 ± 8.6	128 ± 12.8	141 ± 14.7	141 ± 14.7	161 ± 9.4	142 ± 12.9	148 ± 26.9			
≥ 11.0	145 ± 11.1	136 ± 11.7	145 ± 18.7	140 ± 15.0	162 ± 6.0	141 ± 14.4	158 ± 14.2			

Continued

Table 3.--Average moisture content of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation								
		Stem								
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches			
<u>Percent</u>										
Wood and Bark										
5.0-10.9	106 ± 16.4	92 ± 3.8	106 ± 17.4	106 ± 17.4	116 ± 18.2	107 ± 17.0	114 ± 19.8			
≥ 11.0	96 ± 4.9	96 ± 5.6	97 ± 6.5	96 ± 5.2	104 ± 11.2	96 ± 4.8	106 ± 10.7			
HARDWOODS										
Wood										
1.0- 4.9	66 ± 10.1	--	--	--	--	65 ± 10.6	67 ± 9.6			
5.0-10.9	63 ± 8.8	69 ± 10.1	64 ± 9.3	64 ± 9.6	61 ± 9.1	64 ± 9.4	59 ± 7.3			
≥ 11.0	68 ± 11.0	72 ± 13.3	65 ± 9.8	71 ± 13.4	61 ± 6.6	71 ± 13.3	60 ± 5.7			
Bark										
1.0- 4.9	74 ± 22.5	--	--	--	--	73 ± 22.4	80 ± 28.2			
5.0-10.9	66 ± 12.4	61 ± 14.0	61 ± 13.0	61 ± 12.8	69 ± 15.4	63 ± 13.1	74 ± 13.0			
≥ 11.0	58 ± 10.6	55 ± 12.3	56 ± 11.9	55 ± 11.9	61 ± 10.7	55 ± 11.8	62 ± 10.4			
Wood and Bark										
1.0- 4.9	68 ± 7.7	--	--	--	--	67 ± 10.3	71 ± 11.7			
5.0-10.9	63 ± 7.2	68 ± 8.5	63 ± 7.9	64 ± 8.0	63 ± 8.0	64 ± 7.9	64 ± 7.2			
≥ 11.0	66 ± 8.0	69 ± 10.4	63 ± 6.8	68 ± 10.4	60 ± 4.3	68 ± 10.5	60 ± 3.3			
HICKORY										
Wood										
1.0- 4.9	52 ± 3.9	--	--	--	--	51 ± 3.3	56 ± 7.7			
5.0-10.9	52 ± 3.9	61 ± 9.0	53 ± 4.0	53 ± 4.1	50 ± 4.0	52 ± 4.0	52 ± 8.0			
≥ 11.0	54 ± 6.9	57 ± 9.4	51 ± 3.7	56 ± 8.3	51 ± 5.9	56 ± 8.2	51 ± 4.3			
Bark										
1.0- 4.9	76 ± 21.7	--	--	--	--	74 ± 22.5	91 ± 16.2			
5.0-10.9	75 ± 15.8	76 ± 12.3	69 ± 16.6	69 ± 16.8	81 ± 20.0	72 ± 18.3	84 ± 12.6			
≥ 11.0	81 ± 13.6	81 ± 24.4	78 ± 13.6	81 ± 22.1	83 ± 5.8	81 ± 22.0	83 ± 3.5			
Wood and Bark										
1.0- 4.9	60 ± 9.1	--	--	--	--	59 ± 10.1	70 ± 9.3			
5.0-10.9	56 ± 5.1	62 ± 10.4	56 ± 5.4	56 ± 5.6	57 ± 6.4	56 ± 5.8	64 ± 8.1			
≥ 11.0	59 ± 7.6	61 ± 11.0	55 ± 5.4	60 ± 9.8	59 ± 8.4	60 ± 9.8	60 ± 3.3			
POST OAK										
Wood										
5.0-10.9	63 ± 3.4	68 ± 5.0	62 ± 4.7	64 ± 3.9	62 ± 3.3	64 ± 3.9	59 ± 3.7			
≥ 11.0	65 ± 7.0	67 ± 8.9	64 ± 7.3	67 ± 8.6	61 ± 4.0	67 ± 8.5	61 ± 5.0			

Continued

Table 3.--Average moisture content of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip				
<u>Percent</u>										
Bark										
5.0-10.9	63 ± 8.1	56 ± 16.2	60 ± 11.3	60 ± 10.9	67 ± 10.9	62 ± 10.8	65 ± 9.0			
> 11.0	58 ± 9.2	55 ± 11.0	62 ± 11.5	57 ± 11.0	63 ± 9.9	57 ± 10.9	62 ± 6.8			
Wood and Bark										
5.0-10.9	63 ± 2.5	66 ± 2.0	62 ± 5.1	63 ± 2.9	63 ± 3.7	63 ± 2.9	61 ± 4.7			
≥ 11.0	63 ± 4.2	64 ± 5.4	63 ± 4.6	64 ± 5.2	62 ± 3.5	65 ± 5.4	61 ± 3.3			
SCARLET OAK										
Wood										
1.0- 4.9	63 ± 0.0	--	--	--	--	63 ± 0.0	61 ± 0.0			
5.0-10.9	69 ± 6.8	77 ± 7.9	72 ± 6.2	73 ± 7.1	64 ± 6.4	72 ± 7.0	58 ± 5.4			
> 11.0	77 ± 4.9	83 ± 5.4	71 ± 4.6	82 ± 5.6	64 ± 3.8	82 ± 5.6	62 ± 3.6			
Bark										
1.0- 4.9	55 ± 0.0	--	--	--	--	52 ± 0.0	81 ± 0.0			
5.0-10.9	58 ± 4.0	55 ± 6.1	55 ± 4.6	55 ± 4.8	59 ± 5.9	56 ± 4.5	64 ± 8.3			
> 11.0	59 ± 2.8	58 ± 4.0	57 ± 2.7	58 ± 3.7	58 ± 4.4	58 ± 3.7	61 ± 3.8			
Wood and Bark										
1.0- 4.9	61 ± 0.0	--	--	--	--	60 ± 0.0	69 ± 0.0			
5.0-10.9	67 ± 5.8	75 ± 5.8	69 ± 5.5	70 ± 6.2	63 ± 5.5	69 ± 6.2	59 ± 4.8			
> 11.0	73 ± 4.2	79 ± 4.9	69 ± 3.8	78 ± 5.1	63 ± 2.8	78 ± 5.1	62 ± 2.7			
SOUTHERN RED DAK										
Wood										
5.0-10.9	70 ± 4.4	76 ± 6.4	72 ± 4.8	73 ± 4.8	65 ± 3.8	73 ± 4.5	59 ± 3.5			
> 11	76 ± 5.3	83 ± 6.3	72 ± 4.5	82 ± 6.3	63 ± 3.4	82 ± 6.3	63 ± 3.7			
Bark										
5.0-10.9	51 ± 6.8	47 ± 5.0	46 ± 7.0	47 ± 6.4	56 ± 21.1	48 ± 7.2	62 ± 5.2			
> 11.0	46 ± 3.0	43 ± 3.2	43 ± 3.1	43 ± 3.1	51 ± 3.6	43 ± 3.0	51 ± 3.4			
Wood and Bark										
5.0-10.9	66 ± 3.3	70 ± 5.2	67 ± 4.1	68 ± 3.8	62 ± 4.4	68 ± 3.7	60 ± 3.9			
≥ 11.0	70 ± 3.7	76 ± 5.0	66 ± 3.1	75 ± 5.1	60 ± 2.9	75 ± 5.2	59 ± 2.3			

Continued

Table 3. -- Average moisture content of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class	Total tree (inches)	Average and standard deviation													
		Butt to 9-inch top		9-inch to 4-inch top		Butt to 4-inch top		4-inch to tip	Butt to tip	Branches					
<u>Percent</u>															
WHITE OAK															
Wood															
1.0- 4.9	57 ± 3.4	--	--	--	--	--	56 ± 3.5	61 ± 4.4							
5.0-10.9	60 ± 4.1	64 ± 4.9	61 ± 4.4	61 ± 4.4	60 ± 4.2	61 ± 4.3	58 ± 4.8								
≥ 11.0	64 ± 2.8	66 ± 3.9	62 ± 2.7	65 ± 3.8	61 ± 1.9	65 ± 3.7	60 ± 1.6								
Bark															
1.0- 4.9	66 ± 10.3	--	--	--	--	64 ± 11.0	72 ± 11.0								
5.0-10.9	JO ± 11.2	65 i-15.1	65 ± 13.0	65 ± 12.9	74 i-13.6	67 ± 12.5	77 ± 11.1								
≥ 11.0	59 ± 7.5	54 ± 9.4	56 ± 7.0	54 ± 8.9	64 ± 5.9	54 ± 8.8	67 ± 8.2								
Wood and Bark															
1.0- 4.9	58 ± 4.2	--	--	--	--	58 ± 4.2	66 ± 6.4								
5.0-10.9	62 ± 4.5	65 ± 4.4	61 ± 4.8	61 ± 4.8	63 ± 5.9	61 ± 4.7	65 ± 6.1								
≥ 11.0	63 ± 2.8	64 ± 3.6	61 ± 2.8	64 ± 3.5	62 ± 2.0	64 ± 3.5	62 ± 2.7								
ALL SPECIES															
Wood															
1.0- 4.9	71 ± 15.0	--	--	--	--	71 ± 15.7	JO ± 14.6								
5.0-10.9	69 ± 16.7	JO ± 12.0	JO ± 16.7	JO ± 16.7	68 ± 18.7	70 ± 16.9	65 ± 17.2								
≥ 11.0	73 ± 15.1	JJ ± 16.0	71 ± 15.1	76 ± 15.9	68 ± 15.7	76 ± 15.8	68 ± 15.5								
Bark															
1.0- 4.9	78 ± 23.6	--	--	--	--	75 ± 24.2	87 ± 30.4								
5.0-10.9	75 ± 23.7	64 ± 19.0	JO ± 24.4	70 ± 24.2	79 ± 28.3	72 ± 24.8	83 ± 25.6								
≥ 11.0	72 ± 28.5	68 ± 27.0	70 ± 28.9	68 ± 27.7	80 ± 34.9	69 ± 27.9	81 ± 33.9								
Wood and Bark															
1.0- 4.9	72 ± 14.5	--	--	--	--	72 ± 15.2	76 ± 17.1								
5.0-10.9	JO ± 16.3	JO ± 11.1	70 ± 16.4	70 ± 16.4	70 ± 18.6	70 ± 16.7	71 ± 18.0								
≥ 11.0	72 ± 14.9	75 ± 15.2	70 ± 15.1	74 ± 15.0	70 ± 17.7	74 ± 15.1	71 ± 18.5								

Table 4.--Average proportion of wood and bark green weight in bark, by tree component and size class, for hardwood species in the Upland-South

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Butt to 9-inch top		9-inch to 4-inch top		Butt to 4-inch top				
		Stem	4-inch to tip	4-inch to tip	Butt to tip	4-inch to tip	Butt to tip			
<u>Percent</u>										
SOFT HARDWOODS										
1.0- 4.9	20 ± 6.3	--	--	--	--	--	18 ± 6.8	30 ± 5.0		
5.0-10.9	16 ± 2.8	13 ± 3.9	14 ± 4.9	12 ± 3.0	18 ± 3.5	13 ± 3.1	31 ± 5.3			
≥ 11.0	13 ± 3.3	10 ± 3.3	14 ± 8.1	11 ± 3.5	20 ± 4.1	11 ± 3.5	25 ± 5.0			
SWEETGUM										
1.0- 4.9	19 ± 2.3	--	--	--	--	--	17 ± 2.1	32 ± 4.0		
5.0-10.9	15 ± 2.7	--	--	12 ± 2.0	19 ± 3.7	13 ± 2.6	32 ± 4.2			
≥ 11.0	13 ± 3.3	10 ± 4.6	13 ± 3.6	11 ± 4.3	20 ± 3.1	11 ± 4.3	25 ± 4.6			
YELLDW-PDPLAR										
5.0-10.9	19 ± 2.0	15 ± 2.2	17 ± 1.7	17 ± 1.5	21 ± 3.0	17 ± 1.7	34 ± 4.9			
≥ 11.0	15 ± 3.0	12 ± 2.2	18 ± 12.4	13 ± 3.0	22 ± 4.7	13 ± 3.0	27 ± 3.7			
HARD HARDWOODS										
1.0- 4.9	21 ± 7.9	--	--	--	--	--	19 ± 8.5	30 ± 8.3		
5.0-10.9	18 ± 3.4	13 ± 3.5	15 ± 3.1	15 ± 3.7	20 ± 4.3	15 ± 3.6	30 ± 5.0			
≥ 11.0	17 ± 3.3	14 ± 3.4	17 ± 4.4	14 ± 3.4	23 ± 3.9	14 ± 3.4	26 ± 4.1			
HICKDRY										
1.0- 4.9	36 ± 5.9	--	--	--	--	--	35 ± 6.4	40 ± 5.3		
5.0-10.9	24 ± 3.7	17 ± 4.4	19 ± 2.4	20 ± 4.3	25 ± 5.5	21 ± 4.3	35 ± 3.6			
≥ 11.0	19 ± 1.2	14 ± 1.5	17 ± 0.3	14 ± 1.5	27 ± 6.7	14 ± 1.5	28 ± 2.1			
POST OAK										
5.0-10.9	18 ± 1.5	15 ± 1.9	15 ± 2.1	14 ± 1.6	18 ± 2.9	15 ± 1.5	29 ± 2.4			
≥ 11.0	18 ± 3.6	14 ± 4.6	15 ± 5.9	14 ± 4.7	21 ± 2.8	15 ± 4.6	25 ± 5.7			
SCARLET OAK										
1.0- 4.9	27 ± 0.0	--	--	--	--	25 ± 0.0	42 ± 0.0			
5.0-10.9	18 ± 2.0	14 ± 1.3	15 ± 1.6	15 ± 1.6	19 ± 2.5	15 ± 1.6	26 ± 4.9			
≥ 11.0	16 ± 2.2	13 ± 2.1	16 ± 3.7	14 ± 2.4	22 ± 3.8	14 ± 2.4	23 ± 2.5			
SOUTHERN RED DAK										
5.0-10.9	20 ± 1.7	17 ± 1.6	18 ± 2.0	18 ± 2.0	22 ± 3.0	18 ± 1.9	28 ± 4.0			
≥ 11.0	19 ± 1.6	16 ± 1.6	21 ± 2.5	16 ± 1.7	26 ± 3.6	17 ± 1.8	26 ± 2.5			
WHITE OAK										
1.0- 4.9	22 ± 3.0	--	--	--	--	20 ± 2.6	38 ± 4.0			
5.0-10.9	17 ± 1.6	10 ± 1.7	12 ± 1.1	12 ± 1.6	20 ± 2.8	13 ± 1.7	31 ± 3.5			
≥ 11.0	15 ± 1.3	11 ± 1.9	14 ± 2.2	11 ± 1.8	23 ± 2.1	11 ± 1.8	24 ± 3.9			
ALL SPECIES										
1.0- 4.9	21 ± 7.4	--	--	--	--	19 ± 8.0	30 ± 7.3			
5.0-10.9	18 ± 3.5	13 ± 3.5	15 ± 3.3	14 ± 3.7	20 ± 4.2	15 ± 3.6	30 ± 5.0			
≥ 11.0	16 ± 3.7	13 ± 3.7	16 ± 5.8	13 ± 3.7	22 ± 4.3	13 ± 3.7	25 ± 4.4			

Table 5--Average green weight per cubic foot of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South

Tree size class (inches)	Total tree	Average and standard deviation						
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches	
<u>Pounds per cubic foot</u>								
SOFT HARDWOODS								
Wood								
1.0- 4.9	59 ± 5.2	--	--	--	48 ± 0.0	60 ± 6.3	54 ± 6.2	
5.0-10.9	55 ± 6.3	57 ± 10.8	53 ± 13.2	55 ± 7.4	57 ± 5.7	56 ± 6.9	54 ± 6.2	
> 11.0	54 ± 5.7	54 ± 6.2	53 ± 6.9	54 ± 5.9	55 ± 6.0	54 ± 5.9	55 ± 6.1	
Bark								
1.0- 4.9	50 ± 4.5	--	--	--	--	50 ± 6.2	52 ± 6.2	
5.0-10.9	51 ± 7.4	52 ± 4.4	56 ± 7.5	49 ± 9.1	55 ± 8.6	50 ± 8.7	56 ± 4.8	
> 11.0	54 ± 5.1	51 ± 6.4	53 ± 6.5	51 ± 6.3	60 ± 3.8	52 ± 6.3	59 ± 3.9	
Wood and Bark								
1.0- 4.9	57 ± 4.9	--	--	--	--	58 ± 6.3	53 ± 5.2	
5.0-10.9	54 ± 5.7	56 ± 9.2	54 ± 12.5	54 ± 6.7	56 ± 5.3	55 ± 6.4	55 ± 4.9	
> 11.0	54 ± 4.8	53 ± 5.5	53 ± 5.6	53 ± 5.1	56 ± 5.1	53 ± 5.1	56 ± 4.9	
SWEETGUM								
Wood								
1.0- 4.9	60 ± 2.7	--	--	--	48 ± 0.0	59 ± 2.7	61 ± 5.3	
5.0-10.9	58 ± 2.6	--	--	58 ± 2.9	61 ± 4.7	58 ± 2.7	59 ± 2.8	
> 11.0	59 ± 4.6	58 ± 5.9	60 ± 2.4	58 ± 5.4	59 ± 4.1	58 ± 5.3	62 ± 3.4	
Bark								
1.0- 4.9	50 ± 2.2	--	--	--	--	50 ± 3.1	53 ± 4.8	
5.0-10.9	49 ± 4.0	--	--	45 ± 4.9	55 ± 5.8	47 ± 4.4	57 ± 3.0	
> 11.0	49 ± 2.2	46 ± 3.4	48 ± 4.1	46 ± 2.9	59 ± 3.7	46 ± 2.9	58 ± 5.1	
Wood and Bark								
1.0- 4.9	58 ± 2.2	--	--	--	--	58 ± 2.3	59 ± 3.9	
5.0-10.9	57 ± 2.8	--	--	56 ± 3.1	59 ± 4.6	57 ± 2.9	59 ± 2.5	
> 11.0	57 ± 4.1	56 ± 5.3	58 ± 2.4	57 ± 4.8	59 ± 3.4	57 ± 4.7	61 ± 3.2	
YELLOW-POPLAR								
Wood								
5.0-10.9	50 ± 6.2	58 ± 10.6	46 ± 2.9	49 ± 6.8	53 ± 5.4	50 ± 6.5	49 ± 4.2	
> 11.0	49 ± 3.4	49 ± 5.7	47 ± 4.5	49 ± 4.8	53 ± 4.7	49 ± 4.8	50 ± 4.1	
Bark								
5.0-10.9	52 ± 3.0	49 ± 0.4	51 ± 1.5	52 ± 3.8	57 ± 3.3	52 ± 3.7	55 ± 2.4	
> 11.0	52 ± 1.8	49 ± 1.6	52 ± 3.4	49 ± 2.1	58 ± 1.7	49 ± 2.1	57 ± 1.9	

Continued

Table 5.--Average green weight per cubic foot of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to Y-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	u - - - e - -			
Pounds per cubic foot										
Wood and Bark										
5.0-10.9	50 ± 5.4	56 ± U.6	47 ± 2.6	50 ± 6.0	54 ± 4.4	50 ± 5.8	31 ± 3.0			
≥ 11.0	49 ± 2.8	4Y ± 4.9	48 ± 3.1	4Y ± 4.1	54 ± 3.9	4Y ± 4.0	52 ± 3.4			
HARD HARDWOODS										
Wood										
1.0- 4.9	bl ± 5.3	--	--	--	48 ± 0.0	61 ± 5.7	b0 ± 5.0			
5.0-10.9	62 ± 4.0	62 ± Y.1	61 ± 6.2	62 ± 5.6	bl ± 5.1	62 ± 5.2	b3 ± 5.0			
≥ 11.0	62 ± 5.6	62 ± 6.5	b3 ± 6.0	62 ± 6.2	62 ± 4.3	62 ± 6.2	b4 ± 4.0			
Bark										
1.0- 4.9	51 ± 5.9	--	--	--	--	53 ± 7.2	49 ± 7.0			
5.0-10.9	55 ± 4.5	55 ± 4.0	57 ± 6.0	56 ± 5.8	57 ± 6.1	56 ± 5.6	55 ± 5.2			
≥ 11.0	57 ± 5.3	57 ± 6.2	58 ± 6.9	57 ± 6.2	58 ± 5.8	57 ± 6.1	56 ± 4.9			
Wood and Bark										
1.0- 4.0	59 ± 3.0	--	--	--	--	60 ± 4.4	57 ± 4.8			
5.0-10.9	61 ± 4.3	61 ± 8.0	61 ± 5.8	61 ± 5.0	61 ± 4.4	61 ± 4.7	60 ± 3.8			
≥ 11.0	61 ± 5.1	61 ± 6.1	62 ± 5.6	61 ± 5.8	61 ± 4.1	61 ± 5.8	62 ± 3.9			
HICKORY										
Wood										
1.0- 4.0	52 ± 3.7	--	--	--	48 ± 0.0	52 ± 4.0	55 ± 4.4			
5.0-10.9	59 ± 4.6	52 ± 14.1	55 ± 5.6	5Y ± 6.1	58 ± 4.6	59 ± 5.5	58 ± 4.8			
≥ 11.0	61 ± 2.1	63 ± 1.1	59 ± 0.2	62 ± 0.9	57 ± 8.1	62 ± 1.0	57 ± 3.8			
Bark										
1.0- 4.0	58 ± 4.7	--	--	--	--	58 ± 5.3	54 ± 5.5			
5.0-10.9	57 ± 2.1	58 ± 2.5	58 ± 3.0	58 ± 2.5	58 ± 2.5	58 ± 2.3	55 ± 2.1			
≥ 11.0	57 ± 1.0	59 ± 1.9	60 ± 0.3	59 ± 1.8	56 ± 6.0	59 ± 1.7	56 ± 3.3			
Wood and Bark										
1.0- 4.0	54 ± 2.8	--	--	--	--	54 ± 2.8	55 ± 3.3			
5.0-10.9	58 ± 3.6	53 ± 11.9	56 ± 4.8	59 ± 5.1	58 ± 3.6	59 ± 4.5	57 ± 3.6			
≥ 11.0	60 ± 1.8	62 ± 0.6	59 ± 0.1	62 ± 0.5	57 ± 7.8	62 ± 0.5	56 ± 3.6			
POST OAK										
Wood										
5.0-10.9	66 ± 2.0	64 ± 5.3	64 ± 1.6	65 ± 2.6	64 ± 2.8	65 ± 2.2	70 ± 1.7			
≥ 11.0	63 ± 4.4	61 ± 6.3	63 ± 6.0	62 ± 5.9	63 ± 1.4	62 ± 5.8	68 ± 2.6			

Continued

Table 5.--Average green weight per cubic foot of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation							
		Stem							
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches		
- Pounds per cubic foot -									
Bark									
5.0-10.9	50 ± 4.1	53 ± 5.7	54 ± 7.4	50 ± 4.1	50 ± 6.1	50 ± 4.0	50 ± 6.0		
≥ 11.0	51 ± 2.6	53 ± 2.8	51 ± 2.8	52 ± 2.6	49 ± 3.2	52 ± 2.6	50 ± 4.1		
Wood and Bark									
5.0-10.9	62 ± 1.8	62 ± 4.9	63 ± 0.3	62 ± 2.2	60 ± 2.2	62 ± 1.9	62 ± 3.3		
≥ 11.0	60 ± 3.4	60 ± 5.3	61 ± 4.6	60 ± 4.8	59 ± 1.7	60 ± 4.1	62 ± 2.3		
SCARLET OAK									
Wood									
1.0- 4.9	59 ± 0.0	--	--	--	48 ± 0.0	59 ± 0.0	56 ± 0.0		
5.0-10.9	65 ± 2.4	67 ± 3.7	65 ± 2.6	65 ± 2.7	63 ± 3.0	65 ± 2.5	64 ± 3.8		
≥ 11.0	66 ± 3.6	66 ± 4.2	67 ± 5.5	66 ± 4.3	64 ± 2.9	66 ± 4.3	66 ± 2.0		
Bark									
1.0- 4.9	60 ± 0.0	--	--	--	--	61 ± 0.0	54 ± 0.0		
5.0-10.9	59 ± 2.1	59 ± 2.9	63 ± 2.7	61 ± 3.2	60 ± 2.2	61 ± 3.0	56 ± 3.9		
≥ 11.0	62 ± 2.6	63 ± 2.6	64 ± 2.8	63 ± 2.6	62 ± 3.5	63 ± 2.6	59 ± 3.8		
Wood and Bark									
1.0- 4.9	59 ± 0.0	--	--	--	--	59 ± 0.0	55 ± 0.0		
5.0-10.9	64 ± 2.1	66 ± 3.2	64 ± 2.2	64 ± 2.2	62 ± 2.4	64 ± 2.0	62 ± 3.4		
≥ 11.0	65 ± 2.8	66 ± 3.4	66 ± 4.3	66 ± 3.4	64 ± 2.0	66 ± 3.4	64 ± 1.9		
SOUTHERN RED OAK									
Wood									
5.0-10.9	63 ± 2.8	67 ± 1.9	63 ± 1.4	64 ± 3.2	62 ± 2.7	63 ± 3.1	65 ± 2.7		
≥ 11.0	66 ± 1.5	66 ± 1.6	66 ± 2.0	66 ± 1.6	65 ± 2.6	66 ± 1.6	66 ± 1.7		
Bark									
5.0-10.9	56 ± 1.8	54 ± 2.7	56 ± 2.4	56 ± 2.5	61 ± 11.2	57 ± 2.3	56 ± 3.2		
≥ 11.0	60 ± 1.9	60 ± 1.5	62 ± 1.6	60 ± 1.4	62 ± 3.0	61 ± 1.4	59 ± 3.6		
Wood and Bark									
5.0-10.9	62 ± 2.2	64 ± 1.6	62 ± 1.1	62 ± 2.5	61 ± 3.2	62 ± 2.5	62 ± 2.8		
≥ 11.0	65 ± 1.3	65 ± 1.4	65 ± 1.7	65 ± 1.4	64 ± 2.1	65 ± 1.4	64 ± 1.7		

Continued

Table 5.--Average green weight per cubic foot of wood, bark, and wood and bark combined, by tree component and size class, for hardwood species in the Upland-South--Continued

Tree size class (inches)	Total tree	Average and standard deviation						Branches		
		Stem								
		Butt to 9-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip				
Pounds per cubic foot										
WHITE OAK										
Wood										
1.0- 4.9	62 ± 1.8	--	--	--	48 ± 0.0	62 ± 1.9	60 ± 3.5			
5.0-10.9	64 ± 3.8	62 ± 9.3	61 ± 6.3	64 i-4.7	62 ± 4.4	63 ± 4.3	65 ± 3.2			
> 11.0	61 ± 3.0	60 ± 4.4	63 ± 2.8	60 ± 3.9	61 ± 3.0	60 ± 3.9	66 ± 2.2			
Bark										
1.0- 4.9	50 ± 3.6	--	--	--	--	49 ± 3.8	51 ± 4.4			
5.0-10.9	54 ± 3.1	56 ± 5.4	58 ± 2.9	54 ± 3.7	56 ± 4.3	55 ± 3.6	55 ± 5.5			
> 11.0	57 ± 2.5	58 ± 2.4	59 ± 2.2	58 ± 2.3	59 ± 2.1	58 ± 2.2	55 ± 3.2			
Wood and Bark										
1.0- 4.9	59 ± 2.2	--	--	--	--	59 ± 2.0	56 ± 3.6			
5.0-10.9	62 ± 3.2	61 ± 8.2	61 ± 5.4	62 ± 4.1	61 ± 3.7	62 ± 3.7	61 ± 3.2			
> 11.0	61 ± 2.5	60 ± 3.8	62 ± 2.4	60 ± 3.4	60 ± 2.5	60 ± 3.4	63 ± 2.3			
ALL SPECIES										
Wood										
1.0- 4.9	60 ± 5.4	--	--	--	48 ± 0.0	61 ± 5.9	58 ± 6.6			
5.0-10.9	61 ± 6.0	62 ± 9.3	61 ± 7.3	61 i-6.7	60 ± 5.5	61 ± 6.2	61 ± 6.4			
> 11.0	60 ± 6.9	60 ± 7.4	60 ± 7.6	60 ± 7.2	60 ± 5.8	60 ± 7.2	62 ± 6.6			
Bark										
1.0- 4.9	51 ± 5.5	--	--	--	--	52 ± 6.9	50 ± 7.0			
5.0-10.9	54 ± 5.5	55 ± 4.9	57 ± 6.1	54 i-J.2	57 ± 6.8	55 ± 6.8	55 ± 5.1			
> 11.0	56 ± 5.4	55 ± 6.8	57 ± 7.1	56 ± 6.8	58 ± 5.4	56 ± 6.7	57 ± 4.7			
Wood and Bark										
1.0- 4.9	58 ± 4.3	--	--	--	--	59 ± 5.1	56 ± 5.2			
5.0-10.9	60 ± 5.3	61 ± 8.2	60 ± 6.8	60 ± 6.2	60 ± 4.9	60 ± 5.8	59 ± 4.7			
> 11.0	59 ± 6.1	59 ± 6.9	60 ± 6.9	59 ± 6.7	59 ± 5.0	59 ± 6.7	60 ± 5.0			

Table 6.--Average green weight of wood and bark per cubic foot of wood, by tree component and size class, for hardwood species in the Upland-South

Tree size class (inches)	Total tree	Average and standard deviation							
		Stem							
		Butt to Y-inch top	9-inch to 4-inch top	Butt to 4-inch top	4-inch to tip	Butt to tip	Branches		
Pounds per cubic foot									
SOFT HARDWOODS									
1.0- 4.9	73 ± 5.9	--	--	--	50 ± 0.0	73 ± 6.4	77 ± 11.8		
5.0-10.9	66 ± 6.5	66 ± 13.5	61 ± 11.6	63 ± 7.2	70 ± 6.4	64 ± 6.8	78 ± 9.2		
> 11.0	62 ± 5.4	60 ± 5.8	62 ± 7.6	60 ± 5.5	68 ± 7.0	60 ± 5.4	74 ± 9.1		
SWEETGUM									
1.0- 4.9	74 ± 3.1	--	--	--	50 ± 0.0	72 ± 3.1	89 ± 7.1		
5.0-10.9	69 ± 3.0	--	--	66 ± 3.1	75 ± 4.7	67 ± 2.9	87 ± 4.6		
> 11.0	68 ± 4.1	64 ± 5.0	69 ± 2.2	65 ± 4.5	74 ± 3.5	65 ± 4.4	82 ± 8.8		
YELLOW-POPLAR									
5.0-10.9	61 ± 7.1	69 ± 14.1	55 ± 3.4	59 ± 7.6	68 ± 5.2	60 ± 7.2	75 ± 7.6		
> 11.0	58 ± 3.6	56 ± 5.9	59 ± 8.5	56 ± 4.7	68 ± 6.4	57 ± 4.6	69 ± 6.8		
HARD HARDWOODS									
1.0- 4.9	77 ± 5.7	--	--	--	50 ± 0.0	76 ± 5.7	86 ± 9.4		
5.0-10.9	76 ± 6.1	72 ± 11.2	72 ± 7.6	73 ± 6.7	77 ± 5.4	74 ± 6.2	90 ± 6.8		
> 11.0	76 ± 7.1	72 ± 7.9	76 ± 7.6	72 ± 7.5	81 ± 6.3	73 ± 7.5	87 ± 7.2		
HICKORY									
1.0- 4.9	82 ± 4.3	--	--	--	50 ± 0.0	81 ± 3.5	93 ± 7.6		
5.0-10.9	77 ± 5.8	63 ± 15.0	68 ± 6.5	74 ± 7.3	77 ± 4.8	75 ± 6.7	89 ± 7.5		
> 11.0	74 ± 3.6	73 ± 2.6	71 ± 0.01	73 ± 2.4	77 ± 4.0	73 ± 2.4	78 ± 7.5		
POST OAK									
5.0-10.9	81 ± 2.5	75 ± 4.7	76 ± 0.9	76 ± 3.0	78 ± 2.6	76 ± 2.4	99 ± 3.4		
> 11.0	76 ± 3.3	71 ± 4.7	74 ± 3.1	72 ± 4.0	79 ± 2.6	72 ± 3.9	92 ± Y.6		
SCARLET OAK									
1.0- 4.9	80 ± 0.0	--	--	--	50 ± 0.0	79 ± 0.0	96 ± 0.0		
5.0-10.9	78 ± 2.1	78 ± 4.0	76 ± 2.7	76 ± 2.1	77 ± 2.9	76 ± 2.6	87 ± 4.8		
> 11.0	79 ± 2.9	76 ± 3.8	80 ± 4.3	76 ± 3.7	83 ± 3.4	76 ± 3.7	85 ± 3.1		
SOUTHERN RED OAK									
5.0-10.9	79 ± 3.3	80 ± 3.5	78 ± 2.6	78 ± 3.8	79 ± 4.3	78 ± 3.8	91 ± 5.4		
> 11.0	82 ± 1.9	79 ± 1.8	83 ± 3.6	79 ± 1.8	88 ± 3.9	79 ± 1.8	90 ± 3.1		
WHITE OAK									
1.0- 4.9	80 ± 2.4	--	--	--	50 ± 0.0	78 ± 2.1	96 ± 2.8		
5.0-10.9	77 ± 4.7	69 ± 10.8	70 ± 7.2	73 ± 5.4	77 ± 4.7	73 ± 4.9	93 ± 4.2		
> 11.0	72 ± 3.6	67 ± 4.1	73 ± 3.1	68 ± 3.6	79 ± 3.2	68 ± 3.6	87 ± 4.9		
ALL SPECIES									
1.0- 4.9	76 ± 6.1	--	--	--	50 ± 0.0	75 ± 6.0	83 ± 11.0		
5.0-10.9	74 ± 7.7	71 i- 11.4	71 ± 8.6	71 ± 8.0	75 ± 6.4	72 ± 7.5	88 ± 8.9		
> 11.0	72 ± Y.1	69 ± 9.2	72 ± 9.8	69 ± 8.9	77 ± 8.7	69 ± 8.9	83 ± 9.7		

Table 7.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable

Species or species group	Weight green or dry	Regression equation coefficients				Coefficient of determination (R^2)	Standard error ³ ($S_{y \cdot x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²				
		a'	b	a''	b			
TOTAL-TREE YOOD, BARK, AND FOLIAGE								
Soft Hardwoods	Green	4.03305	1.22682	3.76200	1.24133	0.98	0.0957	122
	Dry	2.24316	1.20782	1.58122	1.28073	0.98	0.1023	122
Sweetgum	Green	3.45384	1.26820	3.10274	1.29055	0.99	0.0721	39
	Dry	1.57902	1.28241	1.23675	1.33335	0.99	0.0725	39
Yellow-poplar	Green	1.49817	1.47090	8.55437	1.10762	0.98	0.0678	19
	Dry	0.46515	1.58089	5.84275	1.05322	0.98	0.0764	19
Hard Hardwoods	Green	4.41595	1.21429	3.90893	1.23972	0.99	0.0873	364
	Dry	2.47910	1.23265	3.00118	1.19280	0.99	0.0849	364
Hickory	Green	4.21010	1.19922	0.16719	1.87191	0.99	0.0826	37
	Dry	2.42737	1.22122	0.14027	1.81569	0.99	0.0741	37
Post oak	Green	3.52810	1.24978	11.43392	1.00460	0.98	0.0612	26
	Dry	2.73650	1.24077	6.79066	1.00916	0.98	0.0619	26
Scarlet oak	Green	5.85797	1.18664	3.44343	1.29743	0.98	0.0626	42
	Dry	3.71351	1.16900	2.45847	1.25500	0.98	0.0603	42
South. red oak	Green	3.40229	1.28096	3.77536	1.25927	0.98	0.0552	34
	Dry	1.95177	1.28848	2.60305	1.22844	0.98	0.0580	34
White oak	Green	3.77132	1.24770	11.91623	1.00781	0.99	0.0634	87
	Dry	2.40974	1.23665	7.10021	1.01133	0.99	0.0653	87
All Species	Green	4.31938	1.21728	3.88272	1.23950	0.99	0.0898	486
	Dry	2.40445	1.22954	2.76893	1.20011	0.99	0.0957	486
TOTAL-TREE YOOD AND BARK								
Soft Hardwoods	Green	3.72086	1.23838	3.57667	1.24662	0.98	0.0988	122
	Dry	2.13830	1.21440	1.53461	1.28357	0.98	0.1042	122

Continued

Table 7.—Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable—Continued

Species or species group	Weight green or dry	Regression equation coefficients				Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹	b	Trees > 11.0 in d.b.h. ²	b			
a'		a''						
Sweetgum	Green	3.21390	1.27554	2.83100	1.30200	0.99	0.0717	39
	Dry	1.49799	1.28900	1.18827	1.33730	0.99	0.0725	39
Yellow-poplar	Green	1.38087	1.48551	8.44488	1.10792	0.98	0.0671	19
	Dry	0.44159	1.59040	5.80899	1.05310	0.98	0.0764	19
Hard Hardwoods	Green	4.03700	1.22483	3.70662	1.24263	0.99	0.0868	364
	Dry	2.34325	1.23822	2.81946	1.19965	0.99	0.0849	364
Hickory	Green	3.64420	1.22404	0.18250	1.84836	0.99	0.0755	37
	Dry	2.20539	1.23749	0.14913	1.79919	0.99	0.0705	37
Post oak	Green	3.41839	1.24923	11.08083	1.00401	0.98	0.0619	26
	Dry	2.17824	1.24051	6.65153	1.00744	0.98	0.0624	26
Scarlet oak	Green	5.44452	1.19363	3.10396	1.31080	0.98	0.0637	42
	Dry	3.52314	1.17476	2.25162	1.26812	0.98	0.0613	42
South. red oak	Green	3.20531	1.28487	3.39595	1.27282	0.98	0.0561	34
	Dry	1.88717	1.29016	2.38797	1.24109	0.98	0.0585	34
White oak	Green	3.54192	1.25138	11.44305	1.00685	0.99	0.0649	87
	Dry	2.30393	1.23852	6.86747	1.01079	0.99	0.0669	87
All Species	Green	3.95891	1.22794	3.67112	1.24367	0.99	0.0900	486
	Dry	2.27767	1.23522	2.61138	1.20671	0.99	0.0956	486
TOTAL-TREE WOOD								
Soft Hardwoods	Green	2.87796	1.26330	3.19198	1.24171	0.98	0.1069	122
	Dry	1.65387	1.24218	1.37392	1.28085	0.98	0.1134	122
Sweetgum	Green	2.44440	1.30566	2.84007	1.27437	0.99	0.0738	39
	Dry	1.16893	1.31205	1.16774	1.31226	0.99	0.0741	39
Yellow-poplar	Green	1.01298	1.51067	5.88365	1.14379	0.98	0.0700	19
	Dry	0.31578	1.63008	4.50433	1.07590	0.97	0.0822	19

Continued

Table 7.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable--Continued

Species or species group	Weight green or dry	Regression equation coefficients				Coefficient of determination (R ²)	Standard error ³ (S _{y.x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹	b	a" ²	b			
		a'			b			
Hard Hardwoods	Green	3.19206	1.23440	2.96737	1.24962	0.99	0.0953	364
	Dry	1.89910	1.24155	2.42720	1.19039	0.99	0.0899	364
Hickory	Green	2.28746	1.27496	0.12864	1.87510	0.99	0.0804	37
	Dry	1.47650	1.27922	0.10224	1.83597	0.99	0.0789	37
Post oak	Green	2.82547	1.24606	7.90208	1.03161	0.98	0.0653	26
	Dry	1.87993	1.22618	4.60998	1.03914	0.98	0.0699	26
Scarlet oak	Green	4.20032	1.20942	2.37603	1.32822	0.97	0.0721	42
	Dry	2.74142	1.18539	1.71732	1.28292	0.97	0.0705	42
South. red oak	Green	2.70544	1.27310	2.48291	1.29100	0.98	0.0596	34
	Dry	1.66188	1.26209	1.71414	1.25563	0.98	0.0647	34
White oak	Green	2.63180	1.27928	9.69798	1.00733	0.99	0.0635	87
	Dry	1.73147	1.26591	6.33934	0.99529	0.99	0.0649	87
All Species	Green	3.12186	1.24033	2.95515	1.25177	0.99	0.0983	486
	Dry	1.83012	1.24323	2.20297	1.20456	0.99	0.0995	486

¹Trees < 11.0 inches d.b.h.

$$Y = a' (D^2)^b$$

²Trees > 11.0 inches d.b.h.

$$Y = a'' (D^2)^b$$

Where: Y = component weight in pounds

D = tree d.b.h. in inches

a', a'', b = regression coefficients

³log₁₀ form

Table 8.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable

Species or species group	Weight green or dry	Regression equation coefficients				Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²				
		a'	b	a"	b			
TOTAL-STEM WOOD AND BARK								
Soft Hardwoods	Green	3.06818	1.25087	6.08427	1.10811	0.98	0.1019	122
	Dry	1.76433	1.22669	2.56326	1.14881	0.98	0.1036	122
Sweetgum	Green	2.99399	1.26356	4.45413	1.18073	0.99	0.0773	39
	Dry	1.39136	1.27827	1.90083	1.21321	0.99	0.0776	39
Yellow-poplar	Green	0.99452	1.54032	27.95174	0.84472	0.98	0.0642	19
	Dry	0.30828	1.65371	20.33017	0.78027	0.98	0.0747	19
Hard Hardwoods	Green	3.26963	1.21895	5.42981	1.11318	0.99	0.0879	364
	Dry	1.90929	1.23052	4.47873	1.05274	0.99	0.0863	364
Hickory	Green	3.26299	1.18973	0.27607	1.70471	0.99	0.0650	37
	Dry	1.97974	1.20411	0.24648	1.63853	0.99	0.0584	37
Post oak	Green	2.66234	1.24130	12.23908	0.92322	0.98	0.0584	26
	Dry	1.69741	1.23153	7.48033	0.92226	0.98	0.0567	26
Scarlet oak	Green	5.55694	1.13364	3.18970	1.24940	0.97	0.0695	42
	Dry	3.68422	1.10559	2.38800	1.19600	0.97	0.0655	42
South. red oak	Green	2.75099	1.27903	7.67526	1.06509	0.98	0.0489	34
	Dry	1.60722	1.28419	5.99985	1.00952	0.98	0.050	34
White oak	Green	3.29276	1.20873	11.91547	0.94055	0.98	0.0713	87
	Dry	2.16839	1.19319	7.28460	0.94051	0.98	0.0729	87
All Species	Green	3.23553	1.22507	5.38233	1.11895	0.99	0.0918	486
	Dry	1.86650	1.23090	4.03918	1.06993	0.99	0.0922	486
TOTAL-STEM WOOD								
Soft Hardwoods	Green	2.42210	1.27710	5.58303	1.10297	0.98	0.1105	122
	Dry	1.38138	1.25733	2.45365	1.13754	0.98	U. 1146	122
Sweetgum	Green	2.29915	1.29698	4.65394	1.14994	0.99	0.0794	39
	Dry	1.09577	1.30410	2.00097	1.17854	0.99	0.0793	39

Continued

Table 8.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable--Continued

Species or species group	Weight green or dry	Regression equation coefficients				Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²				
		a'	b	a''	b			
Yellow-poplar	Green	0.76350	1.55963	17.93171	0.90147	0.98	0.0692	19
	Dry	0.23399	1.68334	14.83040	0.81818	0.97	0.0808	19
Hard Hardwoods	Green	2.63218	1.23229	4.53964	1.11864	0.99	0.0942	364
	Dry	1.57213	1.23710	3.99397	1.04269	0.99	0.0898	364
Hickory	Green	2.05646	1.25043	0.20302	1.73323	0.99	0.0766	37
	Dry	1.32501	1.25430	0.17262	1.67926	0.99	0.0707	37
Post oak	Green	2.29090	1.23866	9.79069	0.93579	0.98	0.0651	26
	Dry	1.53010	1.21644	5.81338	0.93810	0.98	0.0700	26
Scarlet oak	Green	4.32486	1.15311	2.47377	1.26959	0.97	0.0757	42
	Dry	2.86586	1.12118	1.84078	1.21348	0.97	0.0727	42
South. red oak	Green	2.28777	1.27543	5.42999	1.09520	0.98	0.0532	34
	Dry	1.38511	1.26487	4.17916	1.03460	0.98	0.0568	34
White oak	Green	2.49577	1.24221	10.84485	0.93588	0.98	0.0694	87
	Dry	1.66285	1.22473	7.09486	0.92221	0.98	0.0711	87
All Species	Green	2.59891	1.24079	4.52737	1.12506	0.98	0.0993	486
	W Y	1.52322	1.24211	3.56592	1.06475	u. 99	0.0973	486

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2)^b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)^b$$

Where: Y = component weight in pounds
 D = tree d.b.h. in inches
 a', a'', b = regression coefficients

log₁₀ form

Table 9.--Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable

Species or species group	Volume wood & bark or wood only	Regression equation coefficients				Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹	Trees ≥ 11.0 in d.b.h. ²	a'	b	a"	b	
TOTAL TREE								
Soft Hardwoods	Wd&Bk wood	0.06522	1.24942	0.06347	1.25510	0.99	0.0898	122
		0.04865	1.28014	0.05379	1.25920	0.99	0.0953	122
Sweetgum	Wd&Bk Wood	0.05751	1.26879	0.04395	1.32488	0.99	0.0681	39
		0.04157	1.30404	0.04230	1.30039	0.99	0.0694	39
Yellow-poplar	Wd&Bk Wood	0.02713	1.49101	0.18444	1.09136	0.99	0.0527	19
		0.02078	1.50826	0.12891	1.12772	0.99	0.0535	19
Hard Hardwoods	Wd&Bk wood	0.06908	1.21558	0.06849	1.21737	0.99	0.0781	364
		0.05287	1.22720	0.05206	1.23040	0.99	0.0845	364
Hickory	Wd&Bk wood	0.06553	1.21345	0.00340	1.83000	0.99	0.0773	37
		0.04299	1.25016	0.00218	1.87161	0.99	0.0770	37
Post oak	Wd&Bk Wood	0.05424	1.25505	0.17109	1.01552	0.99	0.0569	26
		0.03866	1.27544	0.12295	1.03417	0.99	0.0540	26
Scarlet oak	Wd&Bk wood	0.08748	1.18835	0.05709	1.27736	0.98	0.0571	42
		0.06580	1.20640	0.04215	1.29928	0.98	0.0618	42
South. red oak	Wd&Bk Wood	0.05510	1.26919	0.06666	1.22948	0.98	0.0541	34
		0.04528	1.25821	0.04655	1.25243	0.98	0.0574	34
White oak	Wd&Bk Wood	0.06245	1.22881	0.14279	1.05637	0.99	0.0590	87
		0.04249	1.27200	0.11701	1.06075	0.99	0.0569	87
All Species	Wd&Bk wood	0.06851	1.22209	0.06460	1.23433	0.99	0.0822	486
		0.05232	1.23721	0.04915	1.25024	0.99	0.0899	486

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2)b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)b$$

Where: Y = component volume in cubic feet

D = tree d.b.h. in inches

a', a'', b = regression coefficients

³log₁₀ form

Table 10.--Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. as the independent variable

Species or species group	Volume wood & bark or wood only	Regression-equation-coefficients				Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹	Trees > 11.0 in d.b.h. ²	a'	b	a"	b	
TOTAL STEM								
SOR Hardwoods	Wd&Bk wood	0.05285 0.04012	1.26575 1.29801	0.10311 0.09175	1.12640 1.12553	0.99 0.98	0.0960 0.1011	122 122
	Wd&Bk wood	0.05325 0.03900	1.25934 1.29651	0.06568 0.06551	1.21561 1.18838	0.99 0.99	0.0735 0.0740	39 39
Yellow-poplar	Wd&Bk wood	0.01899 0.01531	1.55391 1.56345	0.64612 0.42596	0.81849 0.86990	0.98 0.98	0.0581 0.0604	19 19
	Wd&Bk wood	0.05512 0.04331	1.21273 1.22761	0.09808 0.07816	1.09258 1.10453	0.99 0.99	0.0821 0.0862	364 364
Hard Hardwoods	Wd&Bk wood	0.05852 0.03863	1.17801 1.22470	0.00601 0.00404	1.65242 1.69525	0.99 0.99	0.0690 0.0723	37 37
	Wd&Bk wood	0.04116 0.03094	1.25449 1.27574	0.19370 0.15933	0.93155 0.93402	0.99 0.99	0.0556 0.0549	26 26
Scarlet oak	Wd&Bk wood	0.09125 0.06949	1.12148 1.14390	0.05567 0.04285	1.22451 1.24474	0.98 0.98	0.0638 0.0657	42 42
	Wd&Bk wood	0.04733 0.03824	1.26251 1.26097	0.15024 0.10149	1.02168 1.05743	0.99 0.98	0.0465 0.0514	34 34
White oak	Wd&Bk wood	0.05719 0.03973	1.18974 1.23985	0.13923 0.12270	1.00422 1.00472	0.98 0.99	0.0673 0.0645	87 87
	Wd&Bk Wood	0.05522 0.04319	1.22243 1.24059	0.09217 0.07394	1.11561 1.12846	0.99 0.99	0.0903 0.0962	486 486

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2)b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)b$$

Where: Y = component volume in cubic feet

D = tree d.b.h. in inches

a', a'', b = regression coefficients

³log₁₀ form

Table 11.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables

Species or species group	Weight green or dry	Regression equation coefficients						Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²		a ¹	b	a ²	b	
TOTAL-TREE YOOD, BARK, AND FOLIAGE										
Soft Hard woods	Green	0.36115	0.89632	0.14042	1.09330	0.89632	0.99	0.0875	122	
	Dry	0.20927	0.88203	0.06179	1.13639	0.88203	0.98	0.0965	122	
Sweetgum	Green	0.23532	0.94646	0.06941	1.20103	0.94646	0.99	0.0526	39	
	Dry	0.10413	0.95735	0.02658	1.24205	0.95735	0.99	0.0515	39	
Yellow-poplar	Green	0.23024	0.94707	0.12145	1.08044	0.94707	0.98	0.0678	19	
	Dry	0.05927	1.02331	0.06152	1.01555	1.02331	0.98	0.0715	19	
Hard Hardwoods	Green	0.31320	0.93858	0.10004	1.17655	0.93858	0.99	0.0823	364	
	Dry	0.16886	0.95281	0.07269	1.12855	0.95281	0.99	0.0792	364	
Hickory	Green	0.36164	0.91033	0.01704	1.54726	0.91033	0.99	0.0854	37	
	Dry	0.20243	0.92544	0.01344	1.49088	0.92544	0.99	0.0895	37	
Post oak	Green	0.19430	1.00662	0.23601	0.96607	1.00662	0.98	0.0609	26	
	Dry	0.12835	0.99690	0.14308	0.97425	0.99690	0.98	0.0647	26	
Scarlet oak	Green	0.21961	0.99568	0.18321	1.03347	0.99568	0.99	0.0420	42	
	Dry	0.14984	0.97802	0.13591	0.99836	0.97802	0.99	0.0432	42	
South. red oak	Green	0.11897	1.04858	0.06815	1.16476	1.04858	0.98	0.0554	34	
	Dry	0.06592	1.05647	0.04591	1.13197	1.05647	0.98	0.0572	34	
White oak	Green	0.25611	0.96644	0.18888	1.02993	0.96644	0.99	0.0562	87	
	Dry	0.16690	0.95837	0.11699	1.03246	0.95837	0.99	0.0569	87	
All Species	Green	0.32574	0.92803	0.11479	1.14552	0.92803	0.99	0.0914	486	
	Dry	0.17932	0.93579	0.07785	1.10977	0.93579	0.98	0.1046	486	
TOTAL-TREE WOOD AND BARK										
Soft Hardwoods	Green	0.32357	0.90550	0.13065	1.09460	0.90550	0.99	0.0876	122	
	Dry	0.19618	0.88726	0.05924	1.13694	0.88726	0.98	0.0968	122	

Continued

Table II.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R^2)	Standard error ³ ($S_{y \cdot x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²					
		a'	b	a''	b	c			
Sweetgum	Green	0.21394	0.95284	0.06248	1.20951	0.95284	0.99	0.0478	39
	Dry	0.09695	0.96283	0.02517	1.24401	0.96283	0.99	0.0487	39
Yellow-poplar	Green	0.20548	0.95804	U.11558	1.07802	0.95804	0.98	0.0657	19
	Dry	0.05501	1.03065	0.05976	1.01336	1.03065	0.98	0.0704	19
Hard Hardwoods	Green	0.27912	U.94699	0.09209	1.17821	0.94699	0.99	0.0800	364
	Dry	0.15731	0.95736	0.06728	1.13448	0.95736	0.99	0.0777	364
Hickory	Green	0.29833	0.92890	0.01769	1.51800	0.92890	0.99	0.0809	37
	Dry	0.17792	0.93778	0.01385	1.46999	0.93778	0.99	0.0868	37
Post oak	Green	0.18791	1.00655	0.22936	0.96498	1.00655	0.98	0.0611	26
	Dry	0.12487	11.99690	0.14035	0.97254	0.99690	0.98	0.0649	26
Scarlet oak	Green	0.19944	1.00199	0.16245	1.04476	1.00199	0.99	0.0426	42
	Dry	0.13874	0.98382	0.12294	1.00904	0.98382	0.99	0.0430	42
South. red oak	Green	0.11014	1.05261	0.06056	1.17735	1.05261	0.98	0.0558	34
	Dry	0.06299	1.05871	0.04188	1.14380	1.05871	0.98	0.0572	34
White oak	Green	0.23948	0.96887	0.17887	1.02972	0.46887	0.99	0.0593	87
	Dry	0.15919	0.95963	0.11236	1.03227	0.95963	0.99	0.0593	87
All Species	Green	0.29055	0.93665	0.10571	1.14747	0.93665	0.99	0.0892	486
	Dry	0.16723	0.94050	0.07249	1.11482	0.94050	0.98	0.1028	486
TOTAL-TREE WOOD									
Soft Hardwoods	Green	U.23621	0.92468	0.11041	1.08326	0.92468	0.99	0.0923	122
	Dry	U.14172	0.90909	0.05020	1.12550	0.90909	0.98	0.1007	122
Sweetgum	Green	0.15232	0.97556	0.05739	1.17910	0.97556	0.99	0.0485	39
	Dry	0.07191	0.98024	0.02313	1.21678	0.98024	0.99	0.0492	39
Yellow-poplar	Green	U.14161	U.97772	0.07582	1.10797	0.97772	0.98	0.0653	19
	Dry	0.03583	1.06110	0.04203	1.02780	1.06110	0.98	0.0719	19

Continued

Table II.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²					
Hard Hardwoods	Green	a'	b	a''	b	c	0.99	0.0822	364
	Dry	0.21369	0.95558	0.07231	1.18151	0.95558	0.99	0.0766	364
Hickory	Green	0.16542	0.96957	0.01160	1.52359	0.96957	0.99	0.0683	37
	Dry	0.10653	0.47215	0.00907	1.48569	0.97215	0.99	0.0727	37
Post oak	Green	0.15498	1.00515	0.16576	0.99114	1.00515	0.98	0.0631	26
	Dry	0.10924	0.98774	0.10243	1.00116	0.98774	0.98	0.0695	26
Scarlet. oak	Green	0.14244	1.01912	0.12045	1.05408	1.01912	0.99	0.0495	42
	Dry	0.10107	0.99699	0.09206	1.01645	0.99699	0.99	0.0504	42
South. red oak	Green	0.09406	1.04520	0.04594	1.19461	1.04520	0.98	0.0581	34
	Dry	0.05847	1.03815	0.03284	1.15847	1.03815	0.98	0.0624	34
White oak	Green	0.16808	0.99011	0.13795	1.03131	0.99011	0.99	0.0587	87
	Dry	0.11322	0.98037	0.09452	1.01802	0.98037	0.99	0.0583	87
All Species	Green	0.21990	0.94766	0.08329	1.15009	0.94766	0.99	0.0898	486
	Dry	0.12996	0.94835	0.06072	1.10704	0.94835	0.99	0.0986	486

¹Trees < 11.9 inches d. b. h.

$$Y = a'(D^2 Th)^b$$

²Trees > 11.0 inches d. b. h.

$$Y = a''(D^2)^b (Th)^c$$

Where: Y = component weight in pounds

D = tree d. b. h. in inches

Th = tree total height in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 12.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²					
		a'	b	a''	b	c			
TOTAL - STEM WOOD AND BARK									
Soft Hardwoods	Green	0.25113	0.91865	0.22629	0.94037	0.91865	0.99	0.0718	122
	Dry	0.15247	0.90026	0.10080	0.98656	0.90026	0.99	0.0787	122
Sweetgum	Green	0.19936	0.94686	0.10475	1.08105	0.94686	0.99	0.0436	39
	Dry	0.08996	0.95762	0.04268	1.11308	0.95762	0.99	0.0443	39
Yellow-poplar	Green	0.12997	1.00023	0.33457	0.80307	1.00023	0.99	0.0550	19
	Dry	0.03353	1.07770	0.17805	0.72957	1.07770	0.98	0.0615	19
Hard Hardwoods	Green	0.22328	0.94509	0.14030	1.04198	0.94509	0.99	0.0634	364
	Dry	0.12731	0.95389	0.11160	0.98135	0.95389	0.99	0.0620	364
Hickory	Green	0.28445	0.90361	0.02884	1.38086	0.90361	0.99	0.0639	31
	Dry	0.16984	0.91313	0.02461	1.31586	0.91313	0.99	0.0709	37
Post oak	Green	0.14156	1.00641	0.26456	0.87602	1.00641	0.99	0.0479	26
	Dry	0.09446	0.99578	0.16531	0.87908	0.99578	0.99	0.0505	26
Scarlet oak	Green	0.21820	0.96294	0.19784	0.98336	0.96294	0.99	0.0396	42
	Dry	0.15824	0.93801	0.15837	0.93784	0.93801	0.99	0.0361	42
South. red oak	Green	0.06848	1.05729	0.13946	0.96242	1.05729	0.99	0.0420	34
	Dry	0.05008	1.06363	0.10728	0.90476	1.06363	0.99	0.0422	34
White oak	Green	0.23197	0.94188	0.22015	0.95278	0.94188	0.99	0.0462	87
	Dry	0.15699	0.93059	0.14218	0.95124	0.93059	0.99	0.0462	87
All Species	Green	0.23039	0.93834	0.16198	1.01179	0.93834	0.99	0.0687	486
	Dry	0.13342	0.94104	0.11762	0.96734	0.94104	0.99	0.0799	436
TOTAL - STEM WOOD									
Soft Hardwoods	Green	0.18724	0.93840	0.19494	0.93000	0.93640	0.99	0.0799	122
	Dry	0.11114	0.92387	0.09026	0.96727	0.92387	0.99	0.0865	122
Sweetgum	Green	0.14291	0.97154	0.09876	1.04859	0.97154	0.99	0.0465	39
	Dry	0.06718	0.97669	0.04150	1.07713	0.97669	0.99	0.0467	39

Continued

Table 12.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees \geq 11.0 in d.b.h. ²					
		a'	b	a''	b	c			
Yellow-poplar	Green	0.09541	1.01497	0.20464	0.85586	1.01497	0.99	0.0581	19
	Dry	0.02376	1.10030	0.12069	0.76144	1.10030	0.98	0.0647	19
Hard Hardwoods	Green	0.17309	0.95630	0.11347	1.04436	0.95630	0.99	0.0651	364
	Dry	0.10252	0.95980	0.09821	0.96875	0.95980	0.99	0.0602	364
Hickory	Green	0.15515	0.95176	0.01938	1.38542	0.95176	0.99	0.0551	37
	Dry	0.10000	0.95385	0.01619	1.33348	0.95385	0.99	0.0572	37
Post oak	Green	0.12107	1.00577	0.21433	0.88667	1.00577	0.99	0.0538	26
	Dry	0.08582	0.98691	0.13597	0.89096	0.98691	0.98	0.0611	26
Scarlet oak	Green	0.15648	0.98251	0.14710	0.99540	0.98251	0.99	0.0448	42
	Dry	0.11396	0.95503	0.11833	0.94719	0.95503	0.99	0.0423	42
South. red oak	Green	0.07352	1.05553	0.09979	0.99184	1.05553	0.99	0.0461	34
	Dry	0.04475	1.04948	0.07940	0.92992	1.04948	0.98	0.0486	34
White oak	Green	0.16519	0.96663	0.17835	0.95064	0.96663	0.99	0.0473	87
	Dry	0.11349	0.95393	0.12411	0.93528	0.95393	0.99	0.0468	87
All Species	Green	0.17702	0.95148	0.13157	1.01336	0.95148	0.99	0.0709	486
	Dry	0.10491	0.95101	0.10184	0.95720	0.95101	0.99	0.0776	486

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2 Th)^b$$

²Trees \geq 11.0 inches d.b.h.

$$Y = a''(D^2)^b (Th)^c$$

Where: Y = component weight in pounds

D = tree d.b.h. in inches

Th = tree total height in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 13.--Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone for hardwood species in the Upland-South, with d. b. h. and total height as the independent variables

Species or species group	Volume wood & bark or wood only	Regression equation coefficients						Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d. b. h. ²		a''	b	c		
TOTAL TREE										
Soft Hardwoods	Wd&Bk	0.00555	0.91352	C.00225	1.10191	0.91352	0.99	0.0774	122	
	Wood	0.00385	0.93723	0.00178	1.09782	0.93723	0.99	0.0769	122	
Sweetgum	Wd&Bk	0.00390	0.94730	0.00099	1.23425	0.94730	0.99	0.0451	39	
	Wood	0.00261	0.97370	0.00085	1.20700	0.97370	0.99	0.0451	39	
Yellow-poplar	Wd&Bk	0.00388	0.96524	0.00252	1.05566	0.96524	0.99	0.0462	19	
	Wood	0.00282	0.98015	0.00170	1.08579	0.98015	0.99	0.0415	19	
Hard Hardwoods	Wd&Bk	0.00486	0.94018	0.00175	1.15251	0.94018	0.99	0.0683	364	
	Wood	0.00358	0.95048	0.00130	1.16142	0.95048	0.99	0.0662	364	
Hickory	Wd&Bk	0.00554	0.91970	0.00033	1.50669	0.91970	0.99	0.0909	37	
	wood	0.00331	0.94932	0.00020	1.53200	0.94932	0.99	0.0776	37	
Post oak	Wd&Bk	0.00294	1.01112	0.00348	0.97649	1.01112	0.99	0.0562	26	
	wood	0.00202	1.02657	0.00234	0.99582	1.02657	0.99	0.0547	26	
Scarlet oak	Wd&Bk	0.00333	0.99473	0.00301	1.01585	0.99473	0.99	0.0371	42	
	Wood	0.00233	1.01241	0.00214	1.03074	1.01241	0.99	0.0396	42	
South. red oak	Wd&Bk	0.00196	1.04024	0.00125	1.13479	1.04024	0.98	0.0535	34	
	Wood	0.00162	1.03396	0.00090	1.15637	1.03396	0.98	0.0554	34	
White oak	Wd&Bk	0.00442	0.95184	0.09241	1.07811	0.95184	0.99	0.0513	87	
	wood	0.00274	0.98507	0.00171	1.08362	0.98507	0.99	0.0492	87	
All Species	Wd&Bk	0.00502	0.93368	0.00192	1.13430	0.93368	0.99	0.0724	486	
	Wood	0.00365	0.94707	0.00142	1.14365	0.94707	0.99	0.0691	486	

¹Trees < 11.0 inches d. b. h.

$$Y = a'(D^2 Th)^b$$

²Trees > 11.0 inches d. b. h.

$$Y = a''(D^2)b(Th)c$$

Where: Y = component volume in cubic feet

D = tree d. b. h. in inches

Th = tree total height in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 14 --Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and total height as the independent variables

Species or species group	Volume wood & bark or wood only	Regression equation coefficients					Coefficient of determination (R ²)	Standard error ³ (S _{y-x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹	Trees > 11.0 in d.b.h. ²	a'	b	a''	b	c	
TOTAL STEM									
Soft Hardwoods	Wd&Bk Wood	0.00420 0.00297	0.92948 0.95403	0.00368 0.00304	0.95702 0.94878	0.92948 0.95403	0.99 0.99	0.0628 0.0632	122 122
	Wd&Bk Wood	0.00360 0.00244	0.94307 0.97048	0.00156 0.00138	1.11796 1.08898	0.94307 0.97048	0.99 0.99	0.0403 0.0407	39 39
Yellow-poplar	Wd&Bk wood	0.00237 0.00184	1.01242 1.02105	0.00753 0.00487	0.77123 0.81860	1.01242 1.02105	0.99 0.99	0.0427 0.0418	19 19
	Wd&Bk wood	0.00381 0.00287	0.94038 0.95283	0.00258 0.00198	1.02144 1.03009	0.94038 0.95283	0.99 0.99	0.0545 0.0516	364 364
Hickory	Wd&Bk Wood	0.00529 0.00312	0.89334 0.93041	0.00063 0.00039	1.33677 1.36100	0.89334 0.93041	0.99 0.99	0.0795 0.0690	37 37
	Wd&Bk wood	0.00215 0.00154	1.01535 1.03216	0.00400 0.00308	0.88621 0.88845	1.01535 1.03216	0.99 0.99	0.0474 0.0469	26 26
Scarlet oak	Wd&Bk Wood	0.00382 0.00270	0.94928 0.96937	0.00354 0.00258	0.96525 0.97899	0.94928 0.96937	0.99 0.99	0.0352 0.0354	42 42
	Wd&Bk Wood	0.00159 0.00126	1.04400 1.04474	0.00288 0.00195	0.92004 0.95429	1.04400 1.04474	0.99 0.99	0.0390 0.0433	34 34
White oak	Wd&Bk wood	0.00418 0.00264	0.92756 0.96507	0.00274 0.00204	1.01548 1.01899	0.92756 0.96507	0.99 0.99	0.0388 0.0334	87 87
	Wd&Bk wood	0.00391 0.00290	0.93764 0.95282	0.00283 0.00218	1.00487 1.01248	0.93764 0.95282	0.99 0.99	0.0568 0.0549	486 486

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2 Th)^b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2) b(Th)^c$$

Where': Y = component volume in cubic feet

D = tree d.b.h. in inches

Th = tree total height in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 15.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as independent variables

Species or species group	Weight green or dry	Regression equation coefficients						Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²						
		a ¹	b	a ²	b	c				
TOTAL-TREE WOOD, BARK, AND FOLIAGE										
Soft Hardwoods	Green	3.54118	0.66535	0.32725	1.16192	0.66535	0.97	0.0836	82	
	Dry	1.76873	0.67019	0.16990	1.15871	0.67019	0.97	0.0860	82	
Sweetgum	Green	2.89896	0.68989	0.19264	1.25524	0.68989	0.99	0.0552	29	
	Dry	1.33772	0.69653	0.07635	1.29360	0.69653	0.99	0.0500	29	
Yellow-poplar	Green	1.64985	0.75147	0.22730	1.16479	0.75147	0.98	0.0699	19	
	Dry	0.48641	U. 81473	0.12289	1.10159	0.81473	0.98	0.0706	19	
Hard Hardwoods	Green	3.90351	0.67938	0.30159	1.21330	0.67938	0.97	0.0792	262	
	Dry	2.44712	0.67450	0.20537	1.19117	0.67450	0.97	0.0749	262	
Hickory	Green	4.74083	0.65169	0.07900	1.50544	0.65169	0.98	0.0715	22	
	Dry	3.02318	0.64985	0.05637	1.48016	0.64985	0.98	0.0734	22	
Post oak	Green	2.65935	0.73349	0.85732	U. 96954	0.73349	0.99	0.0561	26	
	Dry	1.70907	0.72670	0.51422	0.97714	0.72670	0.98	0.0598	26	
Scarlet oak	Green	2.62263	0.74803	0.52781	1.08232	0.74803	0.98	0.0593	41	
	Dry	1.65131	0.73922	0.38845	1.04097	0.73922	0.98	0.0573	41	
South. red oak	Green	3.76756	0.686' 37	0.27921	1.22957	0.68697	0.98	0.0636	34	
	Dry	2.11764	0.69359	0.19065	1.19562	0.69359	0.98	0.0642	34	
White oak	Green	3.31255	0.69981	0.58930	1.05982	0.69981	0.98	0.0603	75	
	Dry	2.27314	0.68385	0.34213	1.07873	0.68385	0.98	0.0638	75	
TOTAL-TREE WOOD AND BARK										
Soft Hardwoods	Green	3.07487	0.67891	0.31725	1.15252	0.67891	0.97	0.0808	82	
	Dry	1.62822	0.67795	0.16680	1.15304	U. 67795	0.97	0.0845	82	

Continued

Table 15.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²					
		a'	b	a''	b	c			
Sweetgum	Green	2.59048	0.69929	0.18286	1.25204	0.69929	0.99	0.0520	29
	Dry	1.23894	0.70331	0.07481	1.28862	0.70331	0.99	0.0485	24
Yellow-poplar	Green	1.50540	0.76027	0.21799	1.163211	0.76027	0.98	0.0678	19
	Dry	0.45786	0.82067	0.12004	1.05982	0.82067	0.98	0.0693	19
Hard Hardwoods	Green	3.68781	0.68079	0.27341	1.22330	0.68079	0.97	0.0795	262
	Dry	2.32058	0.67712	0.19005	1.19889	0.67712	0.97	0.0754	262
Hickory	Green	4.28859	0.65886	0.07706	1.49689	0.65886	0.98	0.0710	22
	Dry	2.82527	0.65455	0.05547	1.47412	0.65455	0.98	0.0740	22
Post oak	Green	2.56866	0.73359	0.83382	0.96819	0.73359	0.99	0.0561	26
	Dry	1.66112	0.72683	0.50476	0.97521	0.72683	0.98	0.0598	26
Scarlet oak	Green	2.40363	U.75357	0.47158	1.09317	0.75357	0.98	0.0600	41
	Dry	1.55375	U.74338	0.35318	1.05229	0.74338	0.98	0.0578	41
South. red oak	Green	3.57751	0.68813	0.24867	1.24409	0.68813	0.98	0.0650	34
	Dry	2.07055	0.69313	0.17379	1.20977	0.69313	0.98	0.0656	34
White oak	Green	3.26277	0.69530	0.54277	1.06931	0.69530	0.98	0.0641	75
	Dry	2.22303	0.68177	0.32403	1.08332	0.68177	0.97	0.0664	75
All Species	Green	3.73809	0.67333	0.28657	1.20887	0.67333	0.96	0.0886	344
	Dry	2.33910	0.66674	0.19087	1.18927	0.66674	0.95	0.1021	344
TOTAL-TREE WOOD									
Soft Hardwoods	Green	2.38544	0.69084	0.25886	1.15392	0.69084	0.97	0.0832	82
	Dry	1.24036	0.69379	0.13922	1.14984	0.69379	0.97	0.0865	82
Sweetgum	Green	1.80713	0.72679	0.19016	1.10629	0.72679	0.99	0.0518	29
	Dry	0.86769	11.72999	0.07943	1.22855	0.72999	0.99	0.0466	29
Yellow-poplar	Green	1.08824	0.77505	0.14425	1.19642	0.77505	0.98	0.0685	19
	Dry	0.31915	0.84430	0.08591	1.11796	0.84430	0.98	0.0716	19

Continued

Table 15.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients						Coefficient of determination (R ²)	Standard error ³ (S _{y.x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²		a'	b	a''	b	c
Hard Hardwoods	Green	2.91534	0.68545	0.21197	1.23203	0.68545	0.97	0.0803	262	
	Dry	1.88728	0.67810	1.16124	1.19105	0.67810	0.97	0.0742	262	
Hickory	Green	3.35041	0.65467	0.03611	1.59929	0.65467	0.98	0.0743	22	
	Dry	2.24925	0.65183	0.02757	1.56961	0.65183	0.98	0.0749	22	
Post oak	Green	2.12724	0.73157	0.59799	0.99618	0.73157	0.98	0.0601	26	
	Dry	1.43117	0.71905	0.36175	1.00583	0.71905	0.98	0.0667	26	
Scarlet oak	Green	1.94158	0.75654	0.35071	1.11337	0.75654	0.98	0.0656	41	
	Dry	1.26702	0.74342	0.26448	1.07010	0.74342	0.98	0.0634	41	
South. red oak	Green	3.02525	0.68147	0.18607	1.26294	0.68147	0.98	0.0682	34	
	Dry	1.79660	0.67962	0.13251	1.22322	0.67962	0.97	0.0699	34	
White oak	Green	2.59281	0.70141	0.41247	1.08473	0.70141	0.98	0.0632	75	
	Dry	1.78950	0.68733	0.26814	1.08314	0.68733	0.97	0.0643	75	
All Species	Green	2.91422	0.68080	0.22312	1.21661	0.68080	0.96	0.0869	344	
	Dry	1.84077	0.67317	0.15944	1.18325	0.67317	0.95	0.0961	344	

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2H4)^b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)^b (H4)^c$$

Where: Y = component weight in pounds

D = tree d.b.h. in inches

H4 = tree height to 4-inch top in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 16.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as the independent variables

Species or species group	Weight green or dry	Regression equation coefficients						Coefficient of determination (R ²)	Standard error ³ (S _{y,x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²		a'	b	a"	b	c
TOTAL-STEM WOOD AND BARK										
Soft Hardwoods	Green	2.07910	0.71004	0.60943	0.96593	0.71004	0.98	0.0625	82	82
	Dry	1.09182	0.71037	0.32012	0.96620	0.71037	0.98	0.0641	82	
Sweetgum	Green	2.28022	0.70028	0.31865	1.11062	0.70028	0.99	0.0421	29	29
	Dry	1.09326	0.70418	0.13041	1.14754	0.70418	0.99	0.0398	29	
Yellow-poplar	Green	1.03987	0.79370	0.64878	0.89207	0.79370	0.98	0.0578	19	19
	Dry	0.30693	0.85834	0.36959	0.81960	0.85834	0.98	0.0599	19	
Hard Hardwoods	Green	2.77076	0.68663	0.41666	1.08168	0.68663	0.97	0.0671	262	262
	Dry	1.76422	0.68111	0.31325	1.04152	0.68111	0.98	0.0615	262	
Hickory	Green	3.97910	0.63209	0.09718	1.40614	0.63209	0.98	0.0610	22	2%
	Dry	2.65333	0.62698	0.07544	1.36932	0.62698	0.98	0.0643	22	
Post oak	Green	1.98856	0.72994	0.94179	0.88578	0.72994	0.99	0.0500	26	26
	Dry	1.28931	0.72233	0.58096	0.88855	0.72233	u. 99	0.0523	26	
Scarlet oak	Green	2.18326	0.73512	0.55923	1.01912	0.73512	0.98	0.0565	41	41
	Dry	1.43303	0.72101	0.44084	0.96682	0.72101	0.98	0.0504	41	
South. red oak	Green	3.10349	0.68362	0.56705	1.03806	0.68362	0.98	0.0600	34	34
	Dry	1.77778	0.68887	0.44099	0.97955	0.68887	0.98	0.0594	34	
White oak	Green	2.79743	0.68171	0.64114	0.98889	0.68171	0.99	0.0465	75	75
	Dry	1.92818	0.66675	0.39235	0.99875	0.66675	0.98	0.0484	75	
All Species	Green	2.68331	0.68754	0.44987	1.05991	0.68754	u. 97	0.0699	344	344
	Dry	1.67917	0.68044	0.31739	1.02781	0.68044	0.96	0.0794	344	
TOTAL-STEM WOOD										
Soft Hardwoods	Green	1.70902	0.71769	0.49111	0.97771	0.71769	0.98	0.0659	82	82
	Dry	0.87647	0.72227	0.27134	0.96677	0.72227	0.98	0.0676	82	
Sweetgum	Green	1.63635	0.72702	0.33459	1.05801	0.72702	0.99	0.0444	29	29
	Dry	0.78081	0.73093	0.14543	1.08137	0.73093	0.99	0.0388	29	

Continued

Table 16.--Regression equations for estimating green and dry weight of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as the independent variables--Continued

Species or species group	Weight green or dry	Regression equation coefficients					Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees > 11.0 in d.b.h. ²					
		a'	b	a''	b	c			
Yellow-poplar	Green	0.79244	0.80460	0.39902	0.94766	0.80460	0.98	0.0619	19
	Dry	0.22935	0.87556	0.25336	0.85480	0.87556	0.98	0.0642	19
Hard Hardwoods	Green	2.26533	0.69150	0.33301	1.09129	0.69150	0.97	0.0688	262
	Dry	1.47634	0.68238	0.27223	1.03492	0.68238	0.98	0.0619	262
Hickory	Green	3.08399	0.63520	0.04897	1.49902	0.635213	0.98	0.0662	22
	Dry	2.09677	0.63019	0.03908	1.46054	0.63019	0.98	0.0658	22
Post oak	Green	1.70733	0.72875	0.75914	0.89775	n. 72875	0.98	0.0571	76
	Dry	1.15250	0.71499	0.47005	0.90200	0.71499	0.98	0.0641	26
Scarlet oak	Green	1.78669	0.73961	0.41832	1.04235	0.73961	0.98	0.0615	41
	Dry	1.16989	n. 72363	0.33083	0.98699	n. 72363	0.98	0.0560	41
South. red oak	Green	2.57606	0.68189	11.40428	1.06804	0.68189	0.97	0.0633	34
	Dry	1.50390	0.68060	0.32090	1.00269	0.68060	0.97	0.0631	34
White oak	Dry	2.56032	0.69888	0.32208	0.99661	0.69886	0.98	0.0490	75
All Species	Green	7.18122	0.69393	0.35901	1.07015	0.69393	0.97	0.0704	344
	Dry	1.37237	0.68583	0.77205	1.02328	0.68583	0.97	0.0760	344

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2 H4)b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)b(H4)c$$

Where: Y = component weight in pounds

D = tree d.b.h. in inches

H4 = tree height to 4-inch top in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 17.--Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as the independent variables

Species or species gl vup	Volume wood & bark or wood only	Regression equation coefficients						Coefficient of determination (R ²)	Standard error ³ (S _{y.x})	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees ≥ 11.0 in d.b.h. ²		a"	b	c		
TOTAL TREE										
Soft Hardwoods	Wd&Bk wood	0. 05350	0. 68685	0. 00599	1. 14337	0. 68685	0. 98	0. 0685	82	82
		0. 03968	0. 70315	0. 00467	1. 14913	0. 70315	0. 98	0. 0664	82	
Sweetgum	Wd&Bk Wood	0. 05322	0. 67794	0. 00258	1. 30930	0. 67794	0. 99	0. 0508	29	29
Yellow-poplar	Wd&Bk Wood	0. 02783	0. 77042	0. 00488	1. 13325	0. 77042	0. 99	0. 0413	19	19
Hard Hardwoods	Wd&Bk Wood	0. 05255	0. 69995	0. 00583	1. 15859	0. 69995	0. 98	0. 0645	262	262
Hickory	Wd&Bk wood	0. 06340	0. 68114	0. 00194	1. 40827	0. 68114	0. 98	0. 0711	22	22
Post oak	Wd&Bk wood	0. 04075	0. 73688	0. 01271	0. 97978	0. 73688	0. 99	0. 0507	26	26
Scarlet oak	Wd&Bk wood	0. 03689	0. 75632	0. 00880	1. 05509	0. 75632	0. 98	0. 0540	41	41
South. red oak	Wd&Bk Wood	0. 05978	0. 68306	0. 00507	1. 19731	0. 68306	0. 98	0. 0606	34	34
White oak	Wd&Bk wood	0. 05370	0. 69238	0. 00753	1. 10213	0. 69238	0. 98	0. 0526	75	75
All Species	Wd&Bk Wood	0. 05405	0. 69375	0. 00592	1. 15471	0. 69375	0. 98	0. 0673	344	344
		0. 03952	0. 70720	0. 00448	1. 16091	0. 70720	0. 98	0. 0649	344	

¹Trees < 11.0 inches d. b. h.

$$Y = a'(D^2H4)^b$$

²Trees > 11.0 inches d. b. h.

$$Y = a''(D^2)^b (H4)^c$$

Where: Y = component volume in cubic feet

D = tree d.b.h. in inches

H4 = tree height to 4-inch top in feet

a', a'', b, c = regression coefficients

³log₁₀ foml

Table 18.--Regression equations for estimating cubic-foot volume of total-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and height to a 4-inch top as the independent variables

Species or species group	Volume wood & bark or wood only	Regression-equation coefficients						Coefficient of determination (R^2)	Standard error ³ ($S_{y,x}$)	No. of trees sampled
		Trees < 11.0 in d.b.h. ¹		Trees \geq 11.0 in d.b.h. ²						
		a'	b	a''	b	c				
TOTAL STEM										
Soft Hardwoods	Wd&Bk wood	0.03536 0.02779	0.72107 0.73273	0.01109 0.00865	0.96293 0.97607	0.72107 0.73273	0.99 0.99	0.0572 0.0530	82 82	
Sweetgum	Wd&Bk wood	0.04685 0.03134	0.67939 0.71125	0.00419 0.00433	1.18259 1.12420	0.67939 0.71125	0.99 0.99	0.0404 0.0340	29 29	
Yellow-poplar	Wd&Bk Wood	0.01870 0.01494	0.80795 0.81393	0.01508 0.00977	0.85284 0.90258	0.80795 0.81393	0.99 0.99	0.0371 0.0380	19 19	
Hard Hardwoods	Wd&Bk Wood	0.03875 0.03026	0.70805 0.71687	0.00867 0.00674	1.02015 1.03010	0.70805 0.71687	0.98 0.98	0.0534 0.0545	262 262	
Hickory	Wd&Bk wood	0.05571 0.04034	0.66135. 0.67322	0.00308 0.00174	1.26495 1.32929	0.66135 0.67322	0.98 0.98	0.0683 0.0703	22 22	
Post oak	Wd&Bk Wood	0.03103 0.02348	0.73612 0.74714	0.01437 0.01122	0.89661 0.90116	0.73612 0.74714	0.99 0.99	0.0502 0.0525	26 26	
Scarlet oak	Wd&Bk wood	0.03454 0.02744	0.73300 0.74010	0.01001 0.00739	0.99129 1.01374	0.73300 0.74010	0.98 0.98	0.0495 0.0507	41 41	
South. red oak	Wd&Bk wood	0.05216 0.04169	0.67748 0.67796	0.01154 0.00784	0.99194 1.02624	0.67748 0.67796	0.98 0.98	0.0556 0.0586	34 34	
White oak	Wd&Bk Wood	0.04575 0.03448	0.67960 0.69609	0.00820 0.00611	1.03809 1.05686	0.67960 0.69609	0.99 0.99	0.0348 0.0363	75 75	
All Species	Wd&Bk Wood	0.03809 0.02957	0.71052 0.72099	0.00907 0.00704	1.00957 1.02036	0.71052 0.72099	0.98 0.98	0.0541 0.0542	344 344	

¹Trees < 11.0 inches d.b.h.

$$Y = a'(D^2 H4)b$$

²Trees > 11.0 inches d.b.h.

$$Y = a''(D^2)b(H4)c$$

Where : Y = component volume in cubic feet

D = tree d.b.h. in inches

H4 = tree height to 4-inch top in feet

a', a'', b, c = regression coefficients

³log₁₀ form

Table 19.--Regression equations for estimating green and dry weight of above-stump total-tree wood, bark, and foliage, wood and bark combined, and wood alone for hardwood species in the Upland-South, with d. b. h. and saw-log merchantable height as the independent variables

Species or species group	Weight green or dry	Regression equation coefficients			Coefficient of determination (R^2)	Standard error ² ($S_{y,x}$)	No. of trees sampled
		a	b	c			
TOTAL-TREE WOOD, BARK, AND FOLIAGE							
Soft Hardwoods	Green Dry	5.91933 4.89337	0.96698 0.96429	0.28273 0.16103	0.76 0.78	0.0827 0.0725	27 27
Hard Hardwoods	Green Dry	4.34257 3.29859	1.10688 1.06372	0.19424 0.19016	0.79 0.82	0.0906 0.0812	64 64
Scarlet oak	Green Dry	4.50008 3.48482	1.26048 1.22997	-0.01801 -0.06071	0.90 0.90	0.0671 0.0664	16 16
South. red oak	Green Dry	4.25548 2.83728	1.06916 1.04561	0.29694 0.29471	0.95 0.94	0.0430 0.0485	17 17
All Species	Green Dry	5.39733 5.14974	1.11055 1.10864	0.11443 -0.03275	0.78 0.78	0.0897 0.0869	91 91
TOTAL-TREE WOOD AND BARK							
Soft Hardwoods	Green Dry	5.71324 4.76444	0.96349 0.96090	0.2914 0.16921	0.76 0.78	0.0834 0.0730	27 27
Hard Hardwoods	Green Dry	4.23125 3.24135	1.10605 1.06483	0.19293 0.18669	0.79 0.81	JJ.0924 0.0834	64 64
Scarlet oak	Green Dry	4.37179 3.40532	1.26034 1.23184	-0.01798 -0.06136	0.90 0.89	0.0671 0.0671	16 16
South. red oak	Green Dry	4.13143 2.79562	1.06916 1.04562	0.29694 0.29468	0.95 0.94	0.0430 0.0485	17 17
All Species	Green Dry	5.13749 4.96493	1.10571 1.10631	0.12745 -0.02442	0.77 0.77	0.0907 0.0878	91 91
TOTAL-TREE WOOD							
Soft Hardwoods	Green Dry	5.44089 4.42698	0.96642 0.95742	0.26127 0.15880	0.75 0.78	0.0849 0.0717	27 27
Hard Hardwoods	Green Dry	2.71907 2.00532	1.12091 1.06563	0.24511 0.26913	0.79 0.80	0.0945 0.0872	64 64
Scarlet oak	Green Dry	3.20591 2.51719	1.28066 1.25444	-0.00997 -0.06459	0.87 0.86	0.0779 0.0793	16 16
South. red oak	Green Dry	2.96362 1.89340	1.07662 1.05079	0.32177 0.32947	0.95 0.92	0.0472 t-J.0571	17 17
All Species	Green Dry	3.55229 3.23781	1.10768 1.09063	0.18087 0.07210	0.77 0.78	0.0915 0.0868	91 91

$$^1Y = a(D^2)b(Mh)c$$

Where: Y = component weight in pounds
D = tree d. b. h. in inches

Mh = tree saw-log merchantable height in feet

a,b,c = regression coefficients

²log₁₀ form

Table 20.--Regression equations for estimating green and dry weight of saw-log merchantable-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and saw-log merchantable height as the independent variables

Species or species group	Weight green or dry	Regression equation coefficients ¹			Coefficient of determination (R ²)	Standard error ² (S _{y,x})	No. of trees sampled
		a	b	c			
SAW-LOG STEM WOOD AND BARK							
Soft Hardwoods	Green	0.67303	0.84073	0.90211	0.90	0.0666	27
	Dry	0.56427	0.83732	0.78145	0.90	0.0611	27
Hard Hardwoods	Green	-0.20187	0.98322	0.76167	0.88	0.0712	63
	Dry	0.50667	0.92670	0.76344	0.91	0.0571	63
Scarlet oak	Green	0.74621	0.96120	0.78381	0.99	0.0177	15
	Dry	0.55653	0.93154	0.74518	0.99	0.0204	15
South. red oak	Green	0.99274	0.72002	1.09571	0.96	0.0394	17
	Dry	0.69032	0.68510	1.09425	0.95	0.0447	17
All Species	Green	0.81418	1.01247	0.62653	0.85	0.0777	90
	Dry	0.78474	0.99729	0.49733	0.84	0.0766	90
SAW-LOG STEM YOOD							
Soft Hardwoods	Green	0.67706	0.83804	0.87425	0.88	0.0699	27
	Dry	0.57297	0.82271	0.76992	0.90	0.0592	27
Hard Hardwoods	Green	0.46094			0.88	0.0709	63
	Dry	0.35069	0.9184876	0.84005	0.91	0.0608	63
Scarlet oak	Green	0.63282	0.96894	0.77919	0.99	0.0182	15
	Dry	0.47509	0.93755	0.73525	0.99	0.0223	15
South. red oak	Green	0.73337	0.73219	1.11587	0.96	0.0425	17
	Dry	0.49109	0.69192	1.12206	0.94	0.0516	17
All Species	Green	0.63334	1.00616	0.66992	0.86	0.0761	90
	Dry	0.58154	0.97246	0.58073	0.85	0.0736	90

$$^1Y = a(D^2)^b(Mh)^c$$

Where: Y = component weight in pounds

D = tree d.b.h. in inches

Mh = tree saw-log merchantable height in feet

a, b, c = regression coefficients

$2 \log_{10}$ form

Table 21.--Regression equations for estimating cubic-foot volume of above-stump total-tree wood and bark combined and wood alone for hardwood species in the Upland-South, with d.b.h. and saw-log merchantable height as the independent variables

Species or species group	Volume wood & bark OR wood ally	Regression equation coefficients ¹			Coefficient of determination (R ²)	Standard error ² (S _{y,x})	No. of trees sampled
		a	b	c			
TOTAL TREE							
Soft Hardwoods	Wd&Bk wood	0.10825 0.10687	0.86495 0.87712	0.40355 0.37884	0.76 0.80	0.0773 0.071'2	27 27
	Wd&Bk Wood	0.08048 0.04838	1.04004 1.05517	0.25118 0.31805	0.84 0.84	0.0741 0.0771	64 64
Scarlet oak	Wd&Bk wood	0.08075 0.05731	1.24411 1.26574	-0.04762 -0.03565	0.93 0.92	0.0537 0.0596	16 16
	Wd&Bk Wood	0.08059 0.05694	1.05753 1.06597	0.24323 0.26516	0.95 0.94	0.0441 0.0481	17 17
All Species	Wd&Bk wood	0.08150 0.05324	1.00491 1.00093	0.30523 0.38141	0.82 0.83	0.0745 0.0754	91 91

$$^1Y = a(D^2)b(Mh)^c$$

Where: Y = component volume in cubic feet
 D = tree d.b.h. in inches
 Mh = saw-log merchantable height in feet
 a, b, c = regression coefficients

²log₁₀ form

Table 22.--Regression equations for estimating cubic-foot volume of saw-log merchantable-stem wood and bark combined and wood alone for hardwood species in the Upland-South, with c.b.h. and saw-log merchantable height as the independent variables

Species or species group	Volume wood & bark OR wood only	Regression equation coefficients ¹			Coefficient of determination (R ²)	Standard error ² (S _{y,x})	No. of trees sampled
		a	b	c			
SAW-LOG STEM							
Soft Hardwoods	Wd&Bk Wood	0.01137 0.01208	0.77554 0.76056	1.03036 1.00385	0.92 0.94	0.0586 0.0518	27 27
	Wd&Bk Wood	0.01098 0.00739	0.93232 0.94477	0.82611 0.87744	0.95 0.94	0.0455 0.0368	63 64
Scarlet oak	Wd&Bk Wood	0.01014 0.00739	0.99544 1.03445	0.76001 0.74622	0.99 0.99	0.0218 0.0259	15 16
	Wd&Bk Wood	0.01813 0.01313	0.72081 0.73957	1.03950 1.04975	0.96 0.95	0.0420 0.0443	17 17
All Species	Wd&Bk wood	0.01156 0.00854	0.92196 0.91810	0.82244 0.87447	0.93 0.94	0.0525 0.0495	90 91

$$^1Y = a(D^2)b(Mh)^c$$

Where: Y = component volume in cubic feet
 D = tree d.b.h. in inches
 Mh = saw-log merchantable height in feet
 a, b, c = regression coefficients

²log₁₀ form

Table 23 .-- Regression coefficients for estimating above-stump stem weight to a specified d. o. b. top diameter as a proportion of the total-stem weight for hardwood species in the Upland-South

Species	Regression equation and coefficients ¹					
	Green weight			Dry weight		
	a	b	c	a	b	c
WOOD AND BARK						
Soft Hardwoods	-1.66655	4.50927	-4.50649	-1.59620	4.52339	-4.50157
Sweetgum	-2.19544	4.75749	-4.82010	-2.07716	4.77234	-4.80657
Yellow-poplar	-2.07710	4.79969	-4.93471	-1.97288	4.84199	-4.95434
Hard Hardwoods	-2.28360	4.46072	-4.68636	-2.23719	4.46112	-4.67358
Hickory	-3.09629	4.28856	-4.67482	-3.10193	4.32745	-4.70710
Post oak	-1.91840	4.08257	-4.33818	-1.91071	4.10398	-4.35362
Scarlet oak	-1.95138	4.47389	-4.71628	-2.00681	4.41270	-4.66309
South. red oak	-3.77533	4.00045	-4.43757	-3.83036	3.96024	-4.39942
White oak	-2.07303	4.96243	-5.09445	-2.03925	4.97981	-5.10296
All Species	-2.15806	4.41291	-4.60247	-2.10097	4.42002	-4.59413
WOOD ONLY						
Soft Hardwoods	-1.58330	4.63552	-4.60547	-1.52136	4.63089	-4.58383
Sweetgum	-2.03043	4.91715	-4.93948	-1.93715	4.91375	-4.91348
Yellow-poplar	-2.15028	4.95273	-5.09859	-1.99918	4.96877	-5.08179
Hard Hardwoods	-2.22363	4.57247	-4.78530	-2.20462	4.55367	-4.75886
Hickory	-3.08555	4.39543	-4.77578	-3.13482	4.40292	-4.78594
Post oak	-1.83092	4.17275	-4.40532	-1.83838	4.18398	-4.41261
Scarlet oak	-1.88930	4.56232	-4.78981	-1.97765	4.48821	-4.73111
South. red oak	-3.72423	4.09132	-4.52401	-3.85832	4.02836	-4.47336
White oak	-1.96767	5.13852	-5.24179	-1.95384	5.13262	-5.23190
All Species	-2.09586	4.52930	-4.70413	-2.05976	4.51731	-4.68120

¹Where: $Y_R = \text{stem weight to top d.o.b.} / \text{total-stem weight ratio}$

d = stem specified top d. o. b. in inches

D = tree diameter at breast height in inches

a, b, c = regression coefficients

e = 2.71828 (base of log E)

Table 24 . -- Regression coefficients for estimating above-stump stem volume to a specified d. o. b. top diameter as a proportion of the total-stem volume for hardwood species in the Upland-South

Species	Regression equation and coefficients ¹						
	Wood and bark			Wood only			$\gamma_R = e^{a(d)^b(D)^c}$
	a	b	c	a	b	c	
Soft Hardwoods	-1.58948	4.60349	-4.57456	-0.90981	4.67922	-4.40753	
Sweetgum	-2.20137	4.95909	-5.01335	-1.16784	5.03261	-4.82031	
Yellow-poplar	-1.91229	5.07695	-5.14439	-1.89547	5.27203	-5.32153	
Hard Hardwoods	-2.36727	4.44955	-4.69286	-1.34780	4.43890	-4.44676	
Hickory	-3.14288	4.29374	-4.69551	-1.13635	3.41966	-3.45810	
Post oak	-2.10199	4.06511	-4.36727	-2.04081	4.20585	-4.49028	
Scarlet oak	-2.27238	4.33991	-4.65336	-2.05227	4.47319	-4.73863	
South. red oak	-4.33279	3.90648	-4.40305	-4.55488	3.96664	-4.48531	
White oak	-2.16374	4.91449	-5.07177	-1.62505	4.97019	-5.00555	
All Species	-2.19552	4.43283	-4.62984	-1.20804	4.44103	-4.38550	

¹ Where: γ_R = stem volume to top d.o.b./total-stem volume ratio

d = stem specified top d.o.b. in inches

D = tree diameter at breast height in inches

a, b, c = regression coefficients

e = 2.71828 (base of log E)

Table 25 . -- Regression coefficients for estimating stem weight to a specified d. o. b. top diameter as a proportion of the saw-log stem weight for hardwood species in the Upland-South

Species	Ratio equation and coefficients'					
	$\gamma_R = e^{a(Mh)^b} \left(\left(1 - \frac{d}{.78D}\right)^2 \right)^c$					
	Green weight			Dry weight		
	a	b	c	a	b	c
WOOD AND BARK						
Soft Hardwoods	8.47209	-0.87551	0.38432	11.59248	-0.96035	0.36964
Hard Hardwoods	38.51019	-1.42602	0.31682	41.82526	-1.44736	0.32237
Scarlet oak	4.91463	-0.76090	0.29384	5.88406	-0.80828	0.30559
South. red oak	10.40046	-0.98021	0.30150	11.98108	-1.01939	0.30963
Al 1 Species	17.10465	-1.14320	0.33495	20.83442	-1.19897	0.33719
WOOD ONLY						
Soft Hardwoods	8.18203	-0.87109	0.38393	11.13685	-0.95361	0.37066
Hard Hardwoods	37.96981	-1.42608	0.31456	37.98114	-1.42243	0.31609
Scarlet oak	4.72979	-0.75216	0.29180	4.70978	-0.74676	0.29296
South. red oak	10.13408	-0.97664	0.29890	10.08205	-0.97124	0.30035
Al 1 Species	17.42472	-1.16221	0.33146	19.26726	-1.18010	0.33297

Where: γ_R = ratio of stem weight to top d. o. b. saw-stem

Mh = saw-log merchantable height in feet

d = stem specified top diameter in inches

D = tree diameter at breast height in inches

.78 = constant based on average form class

a, b, c = regression coefficients

e = 2.71828 (base of log E)

Table 26.--Regression coefficients for estimating stem volume to a specified d. o. b. top diameter as a proportion of the saw-log stem volume for hardwood species in the Upland-South

Species	Ratio equation and coefficients ¹					
	v a	Wood and bark b	c	M a	Wood only b	w c
Soft Hardwoods	7.80439	-0.86234	LI.38757	7.35628	-0.85166	0.38766
Hard Hardwoods	35.95983	-1.41022	0.31304	39.34780	-1.45316	0.30980
Scarlet oak	3.88915	-0.61449	0.28986	3.82096	-0.69744	0.29027
South. red oak	7.42641	-0.87619	0.29843	6.88938	-0.85730	0.29543
All Species	16.22161	-1.13382	0.33255	15.94696	-1.13532	0.33040

¹Where: $\gamma_R = e^a(Mh)^b ((1 - (\frac{d}{.78D})^2)^c)$

Mh = saw-log merchantable height in feet

d = stem specified top diameter in inches

D = tree diameter at breast height in inches

.78 = constant based on average form class

a, b, c = regression coefficients

e = 2.71828 (base of log E)

Clark, Alexander, III; Phillips, Douglas R.; Frederick, Douglas J. Weight, volume, and physical properties of major hardwood species in the Upland-South. Res. Pap. SE-257. Asheville, NC: U.S. Department of Agriculture, Forest Service, Southeastern Forest Experiment Station; 1986. 55 pp.

The weight, volume, and physical properties of trees 1 to 20 inches d.b.h. were determined for sweetgum, yellow-poplar, hickory, post oak, scarlet oak, southern red oak, and white oak in northern Alabama and Mississippi, eastern Arkansas, southern Kentucky and Tennessee. Hard hardwoods, soft hardwoods, and individual species equations are presented for predicting green and dry weight and green volume of the total tree above stump and its components. Input variables are d.b.h. and total height, d.b.h. and height to a 4-inch top, d.b.h. and saw-log merchantable height, and d.b.h. alone. Average specific gravity, moisture content, and weight per cubic foot of wood, bark, and wood and bark combined are presented for each species by tree size class and component. Bark percentage is also presented for each species by tree size class and component.

Keywords: Biomass, equations, specific gravity, moisture content, bark percentage, weight per cubic foot.

Clark, Alexander, III; Phillips, Douglas Weight, volume, and physical properties in the Upland-South. Res. Pap. SE-257. Department of Agriculture, Forest Service Station; 1986. 55 pp.

The weight, volume, and physical properties in inches d.b.h. were determined for sweet post oak, scarlet oak, southern red oak, Alabama and Mississippi, eastern Arkansas Tennessee. Hard hardwoods, soft hardwoods equations are presented for predicting green volume of the total tree above stump and total height to a 4-inch top, d.b.h. and saw-log merchantable height, and d.b.h. alone. Average specific gravity, moisture content, and weight per cubic foot of wood, bark, and wood and bark combined are presented for each species by tree size class and component. Bark percentage is also presented for each species by tree size class and component.

Keywords: Biomass, equations, specific gravity, moisture content, bark percentage, weight per cubic foot.



The Forest Service, U.S. Department of Agriculture, is dedicated to the principle of multiple use management of the Nation's forest resources for sustained yields of wood, water, forage, wildlife, and recreation. Through forestry research, cooperation with the States and private forest owners, and management of the National Forests and National Grasslands, it strives -as directed by Congress-to provide increasingly greater service to a growing Nation.

USDA policy does not permit discrimination because of race, color, national origin, sex or religion. Any person who believes he or she has been discriminated against in any USDA-related activity should write immediately to the Secretary of Agriculture, Washington, D.C. 20250.

